



Designation: A131/A131M – 19

Standard Specification for Structural Steel for Ships ¹

This standard is issued under the fixed designation A131/A131M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers structural steel plates, shapes, and bars intended primarily for use in ship construction.

1.2 Material under this specification is available in the following categories:

1.2.1 *Ordinary Strength*—Grades A, B, D, and E with a specified minimum yield point of 34 ksi [235 MPa], and

1.2.2 *Higher Strength*—Grades AH, DH, EH, and FH with a specified minimum yield point of 46 ksi [315 MPa], 51 ksi [350 MPa], or 57 ksi [390 MPa].

1.3 Shapes and bars are normally available as Grades A, B, AH32, and AH36. Other grades may be furnished by agreement between the purchaser and the manufacturer.

1.4 The maximum thickness of products furnished under this specification is 4 in. [100 mm] for plates and 2 in. [50 mm] for shapes and bars.

1.5 When the steel is to be welded, it is presupposed that a welding procedure suitable for the grade of steel and intended use or service will be utilized. See Appendix X3 of Specification **A6/A6M** for information on weldability.

1.6 *Units*—This specification is expressed in both inch-pound units and in SI units; however, unless the purchase order or contract specifies the applicable M specification designation (SI units), the inch-pound units shall apply. The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recom-*

mendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 *ASTM Standards:* ²

A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

E112 Test Methods for Determining Average Grain Size **3.**

Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *control rolling (controlled rolling), n*—a hot deformation process intended to provide austenite (and hence ferrite) grain refinement by careful control of the pass-by-pass temperature/reduction schedule at high temperature regime where austenite recrystallizes after each rolling pass or at lower temperatures where the deformed austenite does not recrystallize between rolling passes, or both. In some cases, rolling may extend below the temperature (A_r^3) at which the transformation from austenite to ferrite begins, so the final rolling passes may involve deformation in the two-phase (austenite + ferrite) region.

3.1.2 *thermo-mechanical controlled processing, n*—a steel treatment that consists of strict control of the steel temperature and the rolling reduction. A high proportion of the rolling reduction is to be carried out close to or below the A_r3 transformation temperature and may involve rolling towards the lower end of the temperature range of the intercritical dual-phase region, thus permitting little if any recrystallization of the austenite. The process may involve accelerated cooling on completion of rolling.

4. Ordering Information

4.1 Specification **A6/A6M** establishes the rules for the ordering information that should be complied with when purchasing material to this specification.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock and Ships.

Current edition approved May 1, 2019. Published May 2019. Originally approved in 1931. Last previous edition approved in 2014 as A131/A131M – 14. DOI: 10.1520/A0131_A0131M-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

4.2 Additional ordering considerations specific to this specification are:

4.2.1 Condition (control rolled or thermo-mechanical control processed, if applicable).

5. Materials and Manufacture

5.1 The steel shall be killed.

5.2 Grades D, E, AH32, AH36, AH40, DH32, DH36, DH40, EH32, EH36, EH40, FH32, FH36, and FH40 shall be made using a fine grain practice. For ordinary-strength grades, aluminum shall be used to obtain grain refinement. For higher-strength grades, aluminum, vanadium, or columbium (niobium) may be used for grain refinement.

5.3 Plates in all thicknesses ordered to Grade E shall be normalized, or thermo-mechanical control processed. Plates over 1 3/8 in. [35 mm] in thickness ordered to Grade D shall be normalized, control rolled, or thermo-mechanical control processed. See Table 1.

5.4 Plates in all thicknesses ordered to Grades EH32 and EH36 shall be normalized, or thermo-mechanical control processed. Plates in all thicknesses ordered to Grade EH40, FH32, FH36, and FH40 shall be normalized, thermo-mechanical control processed, or quenched and tempered. Plates ordered to Grades AH32, AH36, AH40, DH32, DH36, and DH40 shall be normalized, control rolled, thermo-mechanical control processed, or quenched and tempered when so specified. See Table 2.

5.5 In the case of shapes, the thicknesses referred to are those of the flange. Heat treatment and rolling requirements for shapes and bars are given in Table 1 and Table 2.

6. Chemical Composition

6.1 The heat analysis shall conform to the requirements for chemical composition given in Table 3 and Table 4.

6.1.1 When specified, the steel shall conform on product analysis to the requirements given in Table 3 and Table 4, subject to the product analysis tolerances in Specification A6/A6M.

6.2 For thermo-mechanical control process steel, the carbon equivalent shall be determined from the heat analysis and shall conform to the requirements given in Table 5.

7. Metallurgical Requirements

7.1 The steel grades indicated in 5.2 shall be made to fine grain practice, and the requirements for fine austenitic grain size in Specification A6/A6M shall be met.

7.2 Where the use of fine grain practice using columbium (niobium), vanadium, or combinations is permitted in 5.2, one or more of the following shall be met:

7.2.1 Minimum columbium (niobium) content of 0.020 % or minimum vanadium content of 0.050 % for each heat, or

7.2.2 When vanadium and aluminum are used in combination, minimum vanadium content of 0.030 % and minimum acid-soluble aluminum content of 0.010 %, or minimum total aluminum content of 0.015 %.

7.2.3 When columbium (niobium) and aluminum are used in combination, minimum columbium (niobium) content of 0.010 % and minimum acid-soluble aluminum content of 0.010 %, or minimum total aluminum content of 0.015 %.

7.2.4 A McQuaid-Ehn austenitic grain size of 5 or finer in accordance with Test Methods E112 for each ladle of each heat.

8. Mechanical Properties

8.1 Tension Test:

8.1.1 Except as specified in the following paragraphs, the material as represented by the test specimens shall conform to the tensile requirements prescribed in Table 6.

8.1.1.1 Shapes less than 1 in.² [645 mm²] in cross section, and bars, other than flats, less than 1/2 in. [12.5 mm] in thickness or diameter need not be subjected to tension tests by the manufacturer, but chemistry consistent with the required tensile properties must be applied.

8.1.1.2 The elongation requirement of Table 6 does not apply to floor plates with a raised pattern. However, for floor plates over 1/2 in. [12.5 mm] in thickness, test specimens shall be bent cold with the raised pattern on the inside of the

TABLE 1 Condition of Supply and Frequency of Impact Tests for Ordinary-Strength Structural Steel

Grade	Condition of Supply ^B (Frequency of Impact Test) ^C	
	Thickness (t), in. [mm]	t > 2.0 [50]
A	t > 1.0 [25] t # 1.375 [35]	t > 2.0 [50] t # 4.0 [100] CR (50 [45]), TM (50 [45]), TM (25 [23])
	A (-)	TM (50 [45]), TM (25 [23])
D	A (50 [45])	TM (50 [45]), TM (25 [23])
	N (50 [45])	TM (50 [45]), TM (25 [23]) NA ^D
E	N (P), TM (P)	N (P), TM (P)
	N (25 [23]), TM (25 [23]), CR (15 [14])	

^A Product: P = plate; S = shapes and bars.

^B Condition of Supply: A = any condition; AR = as-rolled; N = normalized; CR = control rolled; TM = thermo-mechanical controlled processing. Frequency

^C of Impact Test: (impact test lot size in tons [Mg] from each heat); (-) = no impact test required; (P) = each plate-as-rolled. Condition of supply is not

^D applicable.

^E Impact tests for Grade A are not required if material is produced using a fine grain practice and normalized.

TABLE 2 Condition of Supply and Frequency of Impact Tests for Higher-Strength Structural Steel

Grade	Deoxidation	Grain Refining Element	Product ^A	Condition of Supply ^B (Frequency of Impact Test) ^C					
				Thickness (t), in. [mm]					
				t # 0.5 [12.5]	t > 0.5 [12.5] t # 0.80 [20]	t > 0.80 [20] t # 1.0 [25]	t > 1.0 [25] t # 1.375 [35]	t > 1.375 [35] t # 2.0 [50]	t > 2.0 [50] t # 4.0 [100]
AH32 AH36	Killed, Fine Grain Practice	Cb (Nb) ^E	P	A (50 [45])	N (50 [45]), TM (50 [45]), CR (50 [45])				N (50 [45]), TM (50 [45]), CR (25 [23])
			V	A (50 [45])	N (50 [45]), TM (50 [45]), CR (50 [45]), AR (25 [23])				NA ^D
		Al	P	A (50 [45])	AR (25 [23]), N (50 [45]), TM (50 [45]), CR (50 [45])		N (50 [45]), TM (50 [45]), CR (50 [45])		N (50 [45]), TM (50 [45]), CR (25 [23])
			S	A (50 [45])	AR (25 [23]), N (50 [45]), TM (50 [45]), CR (50 [45])	N (50 [45]), TM (50 [45]), CR (50 [45]), AR (25 [23])		NA ^D	
DH32 DH36	Killed, Fine Grain Practice	Cb (Nb) ^E	P	A (50 [45])	N (50 [45]), TM (50 [45]), CR (50 [45]) N				N (50 [45]), TM (50 [45]), CR (25 [23])
			V	A (50 [45])	(50 [45]), TM (50 [45]), CR (50 [45])				NA ^D
		Al	P	A (50 [45])	AR (25 [23]), N (50 [45]), TM (50 [45]), CR (50 [45])	N (50 [45]), TM (50 [45]), CR (50 [45])		N (50 [45]), TM (50 [45]), CR (25 [23])	
			S	A (50 [45])	AR (25 [23]), N (50 [45]), TM (50 [45]), CR (50 [45])	N (50 [45]), TM (50 [45]), CR (50 [45])		NA ^D	
EH32 EH36	Killed, Fine Grain Practice	Any	P	N (P), TM (P)				N (P), TM (P)	
			S	N (25 [23]), TM (25 [23]), CR (15 [14])				NA ^D	
FH32 FH36	Killed, Fine Grain Practice	Any	P	N (P), TM (P), QT (P)				N (P), TM (P)	
			S	N (25 [23]), TM (25 [23]), QT (25 [23])				NA ^D	
AH40	Killed, Fine Grain Practice	Any	P	A (50 [45])	N (50 [45]), TM (50 [45]), CR (50 [45]) N				N (50 [45]), TM (50 [45]), QT (P)
			S	A (50 [45])	(50 [45]), TM (50 [45]), CR (50 [45])				NA ^D
DH40	Killed, Fine Grain Practice	Any	P	N (50 [45]), TM (50 [45]), CR (50 [45])				N (50 [45]), TM (50 [45]), QT (P)	
			S	N (50 [45]), TM (50 [45]), CR (50 [45]) N				NA ^D	
EH40	Killed, Fine Grain Practice	Any	P	(P), TM (P), CR (P)				N (P), TM (P), QT (P)	
			S	N (25 [23]), TM (25 [23]), CR (25 [23])				NA ^D	
FH40	Killed, Fine Grain Practice	Any	P	N (P), TM (P), QT (P)				N (P), TM (P), QT (P)	
			S	N (25 [23]), TM (25), CR (25 [23])				NA ^D	

^A Product: P = plate; S = shapes and bars.

^B Condition of Supply: A = any condition; AR = as-rolled; TM = thermo-mechanical controlled processing; CR = control rolled; QT = quenched and tempered; N = normalized.

^C Frequency of Impact Test: (impact test lot size in tons [Mg] from each heat); (P) = each plate-as-rolled.

^D Condition of supply is not applicable.

^E Columbium and niobium are considered interchangeable names for the same element and both names are acceptable for use in A01 standards.

specimen through an angle of 180° without cracking when subjected to a bend test in which the inside diameter is three times plate thickness. Sampling for bend testing shall be as specified for the tension tests in 8.1.2.

8.1.2 One tension test shall be made from each of two different plates, shapes, or bars from each heat of structural steel unless the finished product from a heat is less than 50 tons [45 Mg], in which case one tension test is sufficient. If, however, product from one heat differs $\frac{1}{8}$ in. [10 mm] or more in thickness or diameter, one tension test shall be made from both the thickest and the thinnest structural product rolled, regardless of the weight [mass] represented.

8.1.3 For quenched and tempered steel, including Grades EH40, FH32, FH36, and FH40, one tension test shall be made on each plate as quenched and tempered.

8.2 Toughness Tests:

8.2.1 Charpy V-notch tests shall be made on Grade A material over 2 in. [50 mm] in thickness, on Grade B material over 1 in. [25 mm] in thickness and on material over $\frac{1}{4}$ in. [6.4 mm] in thickness of Grades D, E, AH32, AH36, AH40, DH32, DH36, DH40, EH32, EH36, EH40, FH32, FH36, and FH40, as required by Table 1 and Table 2. The frequency of Charpy V-notch impact tests shall be as given in Table 1 and Table 2. The test results shall conform to the requirements given in Table 7.

8.2.2 For Grades EH32, EH36, EH40, FH32, FH36, and FH40 plate material, one set of three impact specimens shall be made from each plate-as-rolled.

8.2.3 For Grade A, B, D, AH32, AH36, AH40, DH32, DH36, and DH40 plate material, and for all shape material, and all bar material, one set of three impact specimens shall be made from the thickest material in each test lot size of each

TABLE 3 Chemical Requirements for Ordinary-Strength Structural Steel

Element	Chemical Composition (heat analysis), % max unless otherwise specified ^A			
	Grade A	Grade B	Grade D	Grade E
	Deoxidation and Thickness (t), in. [mm]			
	Killed	Killed or Semi-Killed	Killed, Fine Grain Practice ^B	Killed, Fine Grain Practice ^B
	t ≤ 2.0 in. [50 mm]	t ≤ 2.0 in. [50 mm]		
		Killed		
		t > 2.0 in. [50 mm]		
C	0.25	0.21	0.21	0.18
Mn	0.60	0.60	0.60	0.70
Si	0.35	0.35	0.10–0.35 ^D	0.10–0.35 ^D
P	0.035	0.035	0.035	0.035
S	0.035	0.035	0.035	0.035
Al (acid soluble)	E	E	E	E
Cb (Nb)	E	E	E	E
V	E	E	E	E
Ti	E	E	E	E
Cu	E	E	E	E
Cr	E	E	E	E
Ni	E	E	E	E
Mo	E	E	E	E
Ca	E	E	E	E
N	0.005	0.005	0.005	0.005
C + Mn/6	0.40	0.40	0.40	0.40

^A Intentionally added elements are to be determined and reported.
^B Grade D steel over 1.0 in. [25 mm] and Grade E steel are to contain at least one of the grain refining elements in sufficient amount to meet the fine grain practice requirements (see Section 7).
^C A maximum carbon content of 0.23 % is acceptable for Grade A shapes and bars.
^D Where the content of acid soluble aluminum is not less than 0.015 %, the minimum required silicon content does not apply.
^E The contents of nickel, chromium, molybdenum, and copper are to be determined and reported. When the amount does not exceed 0.02 %, these elements may be reported as # 0.02 %.

TABLE 4 Chemical Requirements for Higher-Strength Structural Steel

NOTE 1—Where “...” appears in the table, there is no requirement.

Element	Chemical Composition ^A (heat analysis), % max unless otherwise specified	
	Grades AH/DH/EH32, AH/DH/EH36, and AH/DH/EH40	Grades FH32/36/40
	Deoxidation	
	Free Grain Practice ^B	Killed, Fine Grain Practice ^B
C	0.18	0.16
Mn	0.90–1.60 ^C	0.90–1.60
Si	0.50 ^D	0.10–0.50 ^D
P	0.035	0.025
S	0.035	0.025
Al (acid soluble)	0.015	0.015
Cb (Nb)	0.02–0.05	0.02–0.05
V	0.05–0.10	0.05–0.10
Ti	0.02	0.02
Cu	0.35	0.35
Cr	0.20	0.20
Ni	0.40	0.80
Mo	0.08	0.08
Ca	0.005	0.005
N	...	0.009 ^H

^A The contents of any other element intentionally added is to be determined and reported.
^B The steel is to contain at least one of the grain refining elements in sufficient amount to meet the fine grain practice requirement (see Section 7). Grade AH is to contain at least one of the grain refining elements in sufficient amount to meet the fine grain practice requirement (see Section 7).
^C 0.5 in. [12.5 mm] and under in thickness may have a minimum manganese content of 0.70 %.
^D If the content of soluble aluminum is not less than 0.015 %, the minimum required silicon content does not apply.
^E The total aluminum content may be used instead of acid soluble content, in accordance with 7.1.
^F Columbium and niobium are considered interchangeable names for the same element and both names are acceptable for use in A01 standards.
^G The indicated amount of aluminum, columbium (niobium), niobium, and vanadium applies if any such element is used singly. If used in combination, the minimum content in 7.2.2 and 7.2.3, as appropriate, will apply.
^H 0.012 if aluminum is present.
^I This element need not be reported on the mill sheet unless intentionally added.

heat, as required by Table 1 and Table 2. If heat testing is required, a set of three specimens shall be tested for each test lot size indicated in Table 1 and Table 2, of the same type of product produced on the same mill from each heat of steel. The set of impact specimens shall be taken from different as-rolled or heat-treated pieces of the heaviest gage produced. An as-rolled piece refers to the product rolled from a slab, billet, bloom, or directly from an ingot. Where the maximum thickness or diameter of various sections differs by 1/8 in. [10 mm]

or more, one set of impacts shall be made from both the thickest and the thinnest material rolled regardless of the weight represented.

8.2.4 The specimens for plates shall be taken from a corner of the material and the specimens from shapes shall be taken from the end of a shape at a point one third the distance from the outer edge of the flange or leg to the web or heel of the shape. Specimens for bars shall be in accordance with Specification A6/A6M.

**TABLE 5 Carbon Equivalent for Higher-Strength Structural Steel Produced by TMCP**

Grade	Carbon Equivalent, ^A max, %	
	Thickness (t), in. [mm]	
	[50 mm]	t > 2.0 in. [50 mm] t # 4.0 in. [100 mm]
AH32, DH32, EH32, FH32	0.36	0.38
AH36, DH36, EH36, FH36	0.38	0.40
AH40, DH40, EH40, FH40	0.40	0.42

^A The following carbon equivalent formula shall be used to calculate the carbon equivalent, C_{eq} :

$$C_{eq} = C + \frac{Mn}{6} + \frac{Cr}{5} + \frac{Mo}{5} + \frac{V}{15} + \frac{Ni}{15} + \frac{Cu}{15} + \frac{Nb}{10} + \frac{S}{10}$$

8.2.5 The largest size specimens possible for the material thickness are to be machined. The longitudinal axis of each specimen shall be located midway between the surface and the center of the structural product thickness, and the length of the notch shall be perpendicular to the rolled surface of the structural product.

8.2.6 Unless a specific orientation is called for on the purchase order, the longitudinal axis of the specimens may be parallel or transverse to the final direction of rolling of the structural product at the option of the steel manufacturer.

8.2.7 The impact test shall be made in accordance with the Charpy Impact Testing section in Test Methods and Definitions A370.

8.2.8 Each impact test shall constitute the average value of three specimens taken from a single test location. The average value shall meet the specified minimum average with not more than one value below the specified minimum average but in no case below 70 % of the specified minimum average.

8.2.8.1 If the results fail to meet the preceding requirements but 8.2.8.1 (2) and (3) are complied with, three additional specimens may be taken from the location as close to the initial specimens as possible and their test results added to those previously obtained to form a new average. The structural product represented may be accepted if for the six specimens 8.2.8.1 (1), (2), and (3) are met.

(1) The average is not less than the required minimum average.

(2) No more than two individual values are below the required minimum average.

(3) No more than one individual value is below 70 % of the required minimum average.

8.2.8.2 If the required energy values are not obtained upon retest, the material may be heat treated at the option of the producer in the case of as-rolled material or reheat treated in the case of heat-treated material.

8.2.8.3 After heat treatment or reheat treatment, a set of three specimens shall be tested and evaluated in the same manner as for the original material.

8.2.8.4 If the impact test result fails to meet the requirement for the thickest product tested when heat testing, that material shall be rejected and the next thickest material may be tested to qualify the balance of the heat in accordance with 8.2.8. At the option of the producer, retests may be made on each piece of the rejected material, in which case each piece shall stand on the results of its own test. It shall also be the option of the producer to heat treat the product prior to retesting if desired.

9. General Requirements for Delivery

9.1 Material furnished under this specification shall conform to the requirements of the current edition of Specification A6/A6M, for the specific structural product ordered, unless a conflict exists in which case this specification shall prevail.

10. Plate Conditioning

10.1 After removal of any imperfection preparatory to welding the thickness of the plate at any location must not be reduced by more than 20 % of the nominal thickness of the plate.

11. Test Reports

11.1 The test report shall show the results of each test required by Sections 7 and 8, except that the results of only one set of tests need be reported when the amount of material from a heat in a shipment is less than 10 tons [9 Mg] and when the thickness variations described in Section 8 are not exceeded.

11.2 The thickness of the product tested may not necessarily be the same as an individual ordered thickness since it is the heat that is tested rather than each ordered item.

12. Marking

12.1 Plates produced to a normalized heat treatment condition shall be marked with the suffix **N** to indicate that the plates have been normalized.

12.2 Plates produced to a control rolled condition shall be marked with the suffix **CR** to indicate that the plates have been control rolled.

12.3 Plates produced to a thermo-mechanical control processed condition shall be marked with the suffix **TM** to indicate that the plates have been thermo-mechanical control processed.

12.4 Plates produced to a quenched and tempered heat treatment condition shall be marked with the suffix **QT** to indicate that the plates have been quenched and tempered.

13. Keywords

13.1 bars; higher strength; ordinary strength; plates; rivets; shapes; ship construction; steel; structural steel



TABLE 6 Tensile Requirements for Ordinary-Strength and Higher-Strength Structural Steel

Grade	Tensile Strength, ksi [MPa]	Yield Point, min, ksi [MPa]	Thickness in. [mm] Exceeding	Thickness in. [mm] Not Exceeding	Elongation in 8 in. [200 mm], ^A min, %	Elongation in 2 in. [50 mm], ^{A,B} min, %
<i>Ordinary Strength:</i>						
A, B, D, E	58 to 75 [400 to 520] ^C	34 [235]		0.20 [5]	14	22
			0.20 [5]	0.40 [10]	16	22
			0.40 [10]	0.60 [15]	17	22
			0.60 [15]	0.80 [20]	18	22
			0.80 [20]	1.0 [25]	19	22
			1.0 [25]	1.2 [30]	20	22
			1.2 [30]	1.6 [40]	21	22
			1.6 [40]	2.0 [50]	22	22
<i>Higher Strength:</i>						
AH32, DH32, EH32, FH32	64 to 85 [440 to 590]	46 [315]		0.20 [5]	14	20
			0.20 [5]	0.40 [10]	16	20
			0.40 [10]	0.60 [15]	17	20
			0.60 [15]	0.80 [20]	18	20
			0.80 [20]	1.0 [25]	19	20
			1.0 [25]	1.2 [30]	20	20
			1.2 [30]	1.6 [40]	21	20
			1.6 [40]	2.0 [50]	22	20
AH36, DH36, EH36, FH36	71 to 90 [490 to 620]	51 [355]		0.20 [5]	13	20
			0.20 [5]	0.40 [10]	15	20
			0.40 [10]	0.60 [15]	16	20
			0.60 [15]	0.80 [20]	17	20
			0.80 [20]	1.0 [25]	18	20
			1.0 [25]	1.2 [30]	19	20
			1.2 [30]	1.6 [40]	20	20
			1.6 [40]	2.0 [50]	21	20
AH40, DH40, EH40, FH40	74 to 94 [510 to 650]	57 [390]		0.20 [5]	12	20
			0.20 [5]	0.40 [10]	14	20
			0.40 [10]	0.60 [15]	15	20
			0.60 [15]	0.80 [20]	16	20
			0.80 [20]	1.0 [25]	17	20
			1.0 [25]	1.2 [30]	18	20
			1.2 [30]	1.6 [40]	19	20
			1.6 [40]	2.0 [50]	20	20

^A Elongation is not required for floor plate.

^B For nominal thickness up to 4.0 in. [100 mm] plates and wide flats, the specified percentage of elongation in 2 in. [50 mm] shall be applied. For nominal thickness or diameter over 3.5 in. [90 mm] sections and bars, a deduction from the specified percentage of elongation in 2 in. [50 mm] shall be made. See elongation requirement adjustments under Tension Test section of Specification A6/A6M for deduction values.

^C For Grade A shapes and bars, the upper limit of tensile strength may be 80 ksi [550 MPa].



SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A131/A131M – 14) that may impact the use of this standard. (Approved May 1, 2019.)

(1) Revised 1.1, 7.2, and 11.1.

(2) Revised Table 1 to delete minimum thickness of >0.25 in. [6.4 mm].

(3) Revised Table 2 to delete minimum thickness of >0.25 in. [6.4 mm], added limit at 0.80 in [20 mm] for AH32/AH36 Plate products for A supply condition, to modify maximum limit for AH32/AH36 Plate products for supply conditions AR, N, TM, CR from 1.0 in. [25 mm] to 1.375 in [35 mm], to delete AH32/AH36 Sections products cell boundary at 1.0 in. [25 mm] since supply conditions for the two adjacent cells were identical, to delete QT supply condition for FH32/FH36 Plate products for thickness exceeding 2.0 in. [50 mm], to delete vertical cell boundary for DH40 P and S products at 0.5 in. [12.5 mm], to delete EH40 Plate products supply condition QT

in cell with maximum thickness to 2.0 in. [50 mm], to correct typographic error of undefined QQT supply condition for FH40 Plate products, and to add Footnote E regarding interchangeability of columbium and niobium.

(4) Revised the title of Sections 6, 7, and 8.

(5) Revised Table 4 to provide note related to meaning of ellipses in table, to note interchangeability of columbium and niobium, to revise limit for molybdenum for Grades FH32/36/ 40, to add requirement for calcium and associated footnote, and to add footnote regarding interchangeability of columbium and niobium.

(6) Revised Table 6 to provide elongation requirements in 8 in. [200 mm] as a function of product thickness and to modify footnote information.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>