



Designation: A481 – 05 (Reapproved 2020)

Standard Specification for Chromium Metal¹

This standard is issued under the fixed designation A481; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers several grades of chromium metal.

1.2 The values stated in inch-pound units are to be regarded as the standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A1025/A1025M Specification for Ferrous Alloys and Other Alloying Materials, General Requirements](#)

[E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves](#)

[E363 Test Methods for Chemical Analysis of Chromium and Ferrochromium](#)

3. General Conditions for Delivery

3.1 Materials furnished to this specification shall conform to the requirements of Specification [A1025/A1025M](#), including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification [A1025/A1025M](#) constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification [A1025/A1025M](#), this specification shall prevail.

¹ This specification is under the jurisdiction of ASTM Committee [A01](#) on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee [A01.18](#) on Castings.

Current edition approved March 1, 2020. Published March 2020. Originally approved in 1963. Last previous edition approved in 2015 as A481 – 05 (2015). DOI: 10.1520/A0481-05R20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Chemical Composition

4.1 The various grades shall conform to the requirements as to chemical composition specified in [Tables 1 and 2](#).

4.2 The manufacturer shall furnish an analysis of each shipment showing the elements specified in [Table 1](#).

4.3 The values shown in [Table 2](#) are expected maximums. Upon request of the purchaser, the manufacturer shall furnish an analysis for any of these elements on a cumulative basis over a period mutually agreed upon between the manufacturer and the purchaser.

5. Size

5.1 The various grades are available in sizes as listed in [Table 3](#).

5.2 The sizes listed in [Table 3](#) are typical as shipped from the manufacturer's plant. These alloys exhibit varying degrees of friability; therefore, some attrition may be expected in transit, storage, and handling. A quantitative test is not available for rating relative friability of ferrous alloys. A code system has been developed, therefore, for this purpose, and a number rating each product type is shown in the last column of [Table 3](#). Definitions applicable to these code numbers are given in Specification [A1025/A1025M](#).

6. Chemical Analysis

6.1 The chemical analysis of the material shall be made in accordance with the procedure for the ferrous alloys as described in Test Methods [E363](#) or alternative methods, agreed upon by the purchaser and supplier, that will yield equivalent results.

6.2 If alternative methods of analysis are used, in case of discrepancy, Test Methods [E363](#) shall be used for referee.

6.3 Where no method is given in Test Methods [E363](#) for the analysis for a particular element, the analysis shall be made in accordance with a procedure agreed upon between the manufacturer and the purchaser.

7. Keywords

7.1 chromium; chromium metal

TABLE 1 Chemical Requirements

Element	Composition, %	
	Grade A	Grade B
Chromium, min	99.0	99.4
Carbon, max	0.050	0.050
Silicon, max	0.15	0.10
Sulfur, max	0.030	0.010
Phosphorus, max	0.010	0.010

TABLE 2 Supplementary Chemical Requirements

Element	Composition, %	
	Grade A	Grade B
Nitrogen, max	0.050	0.020
Iron, max	0.35	0.35
Manganese, max	0.01	0.01
Hydrogen, max	0.01	0.003
Oxygen, max	0.50	0.10
Vanadium, max	0.050	0.050
Copper, max	0.01	0.01
Molybdenum, max	0.050	0.01
Columbium, max	0.050	0.050
Tantalum, max	0.050	0.003
Cobalt, max	0.003	0.001
Aluminum, max	0.30	0.10
Titanium, max	0.050	0.003
Zirconium, max	0.050	0.003
Arsenic, max	0.005	0.003
Lead, max	0.003	0.001
Tin, max	0.001	0.001
Zinc, max	0.005	0.003
Boron, max	0.005	0.003
Antimony, max	0.005	0.003
Silver, max	0.003	0.001
Bismuth, max	0.003	0.001

TABLE 3 Standard Sizes and Tolerances

Product	Grade	Standard Sizes	Tolerances ^A	Friability Rating
Chromium Metal	A	Plate 2 in. by down	10 %, max retained on 2-in. (50-mm) sieve 10 %, max passing U.S. No. 8 (2.36-mm) sieve	2
	A and B	1 in. by down	15 %, max retained on 1-in. (25.0-mm) sieve 15 %, max passing U.S. No. 8 (2.36-mm) sieve	
		¼ in. by down	5 %, max retained on ¼-in. (6.3-mm) sieve	
		8 mesh by down	5 %, max retained on U.S. No. 8 (2.36-mm) sieve	
		20 mesh by down	5 %, max retained on U.S. No. 20 (850-µm) sieve	
	B	Pellets 1½ in. by 1 in. by 1 in.	Designated by manufacturer	

^A Specifications of sieve sizes used to define tolerances herein are as listed in Specification E11.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>