



Designation: B908 – 19

Standard Practice for the Use of Color Codes for Zinc Casting Alloy Ingot¹

This standard is issued under the fixed designation B908; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This standard is published with the following objectives:

1.2 To establish standard color codes for the Zinc Die Casting and Foundry industry, and

1.3 To standardize the use and application of these color codes.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following documents of the issue in effect on date of order acceptance form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*²

[B240 Specification for Zinc and Zinc-Aluminum \(ZA\) Alloys in Ingot Form for Foundry and Die Castings](#)

[B275 Practice for Codification of Certain Zinc, Tin and Lead Die Castings](#)

[B327 Specification for Master Alloys Used in Making Zinc Die Casting Alloys](#)

[B792 Specification for Zinc Alloys in Ingot Form for Slush Casting](#)

[B793 Specification for Zinc Casting Alloy Ingot for Sheet Metal Forming Dies and Plastic Injection Molds](#)

[B892 Specification for ACuZinc5 \(Zinc-Copper-Aluminum\) Alloy in Ingot Form for Die Castings](#)

[B899 Terminology Relating to Non-ferrous Metals and Alloys](#)

[B952 Specification for Zinc Alloys in Ingot Form for Spin Casting](#)

[B989 Specification for High Fluidity \(HF\) Zinc-Aluminum Alloy in Ingot Form for Thin Wall Die Castings](#)

[E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)

2.3 *ISO Standard:*

[ISO 301 Zinc alloy ingots intended for casting, 1981-05-15](#)³

2.4 *CEN Standard:*

[EN 1774 Zinc and zinc alloys—Alloys for foundry purposes—Ingot and liquid, September 1997](#)⁴

3. Terminology

3.1 Terms shall be defined in accordance with Terminology [B899](#).

4. Significance and Use

4.1 The purpose of these color codes is to allow for quick identification of ingot bundles or jumbo ingots of zinc casting alloys. Other than jumbo ingots, this standard is not intended to imply that each ingot will be color coded but only that each ingot bundle be color coded.

4.2 Each ingot bundle or jumbo ingot shall be identified with the appropriate color code listed in [Table 1](#).

4.3 The color will be applied as a stripe, or stripes, near the corners on opposite ends of two adjacent sides of the ingot bundle or jumbo ingot. The color stripes will be applied to include the ingot bundle foot.

4.4 When using multiple stripes, the colored stripes will be applied from left to right as indicated in [Table 1](#).

¹ This practice is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.04 on Zinc and Cadmium.

Current edition approved July 1, 2019. Published July 2019. Originally approved in 2000. Last previous edition approved in 2014 as B908 – 14. DOI: 10.1520/B0908-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ "English Version" available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁴ "English Version" available from Global Engineering Documents, 15 Inverness Way, East Englewood, CO 80112-5704, <http://global.ihs.com>.

TABLE 1 Color Codes

| Common | UNS ^A | ASTM Standard | ASTM Alloy | Traditional | Color Code | |
|---|------------------|---------------|-----------------------|-----------------------|----------------------------|---------------------------------|
| | | | | | North America ^B | International |
| Alloy 3 | Z33521 | B240 | AG 40A ^C | Zamak 3 | None | White/Yellow ^D |
| Alloy 7 | Z33522 | B240 | AG 40B ^C | Zamak 7 | Brown | White/Brown ^E |
| Alloy 5 | Z35530 | B240 | AC 41A ^C | Zamak 5 | Black | White/Black ^D |
| Alloy 2 | Z35540 | B240 | AC 43A ^C | Zamak 2 | Green | White/Green ^D |
| ZA-8 | Z35635 | B240 | ZA-8 | ZA-8 | Blue | White/Blue ^D |
| ZA-12 | Z35630 | B240 | ZA-12 | ZA-12 | Orange | White/Orange ^D |
| ZA-27 | Z35840 | B240 | ZA-27 | ZA-27 | Purple | White/Purple ^D |
| ACuZinc 5 | Z46540 | B892 | Zn-Cu5-Al3 | ACuZinc5 ^F | Red | White/Red ^E |
| V12 | Z33730 | B327 | V12 | V12 | Pink | White/Pink ^E |
| V12-5 | | B327 | V12-5 | V12-5 | Pink/Black | White/Pink/Black |
| Slush Casting Alloy A | Z34510 | B792 | Slush Casting Alloy A | Slush Casting Alloy A | Black/Red | White/Black/Red ^E |
| Slush Casting Alloy B | Z30500 | B792 | Slush Casting Alloy B | Slush Casting Alloy B | Black/Orange | White/Black/Orange ^E |
| Zinc Casting Alloy for Dies and Molds - A | Z35543 | B793 | Die & Mold Alloy A | Kirksite A | Green/Red | White/Green/Red ^E |
| Zinc Casting Alloy for Dies and Molds - B | Z35542 | B793 | Die & Mold Alloy B | Kirksite B | Green/Black | White/Green/Black ^E |
| HF | | B989 | High Fluidity Alloy | HF | Red/Brown | White/Red/Brown |
| SC-A | Z35550 | B952 | Alloy SC-A | SC-A | Green/Black | White/Green/Black |
| SC-B | Z35551 | B952 | Alloy SC-B | SC-B | Green/Purple | White/Green/Black |
| SC-C | Z35534 | B952 | Alloy SC-C | SC-C | Green/Yellow | White/Green/Yellow |
| SC-D | Z35547 | B952 | Alloy SC-D | SC-D | Green/Blue | White/Green/Blue |
| SC-E | Z35548 | B952 | Alloy SC-E | SC-E | Green/Red | White/Green/Red |
| SC-F | Z35552 | B952 | Alloy SC-F | SC-F | Green/Orange | White/Green/Orange |
| ZA-73 ^G | Z56500 | B952 | ZA-73 | ZA-73 | Blue/Orange | White/Blue/Orange |

^A UNS assignments were established in accordance with Practice E527. The last digit of a UNS number differentiates between alloys of similar composition.

^B The North American system is design to be a simplified version of the International system by eliminating the leading white stripe and in the case of Alloy 3 eliminating all stripes.

^C ASTM alloy designations established in accordance with Practice B275.

^D The color codes for these alloys are adapted from European standard (CEN) specification EN 1774. No color coding currently exists in International standard ISO 301.

^E These alloys are not currently included in European standard EN 1774 nor International standard ISO 301 and no color codes have previously been assigned.

^F ACuZinc and ACuZinc5 are registered names of the General Motors Corporation.

^G ZA-73 is also often used as a hot-chamber die casting alloy and foundry casting alloy.

4.5 In the absence of a written agreement to the contrary between the supplier and end user, the North American color code will be the standard for all North American transactions; for all other transactions the International Color Code will be used.

Zamak; Zamak 2; Zamak 3; Zamak 5; Zamak 7; zinc; zinc alloys; zinc-aluminum alloys; zinc-copper-aluminum alloys

5. Keywords

5.1 ACuZinc; ACuZinc5; color; color code; HF; high fluidity; Kirksite; Kirksite A; Kirksite B; non-ferrous metals;

SUMMARY OF CHANGES

Committee B02 has identified the location of selected changes to this standard since the last issue (B908 – 14) that may impact the use of this standard. (Approved July 1, 2019.)

(1) Added specification listing for HF alloy in Section 2.2 and Table 1.

(2) Expanded Section 4.3 for clarity.

(3) Added HF and high fluidity to Keywords.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>