



Designation: C772 – 03 (Reapproved 2019)

Standard Test Method for Oil Migration or Plasticizer Bleed-Out of Preformed Tape Sealants¹

This standard is issued under the fixed designation C772; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a laboratory procedure that can be used to determine the oil migration or plasticizer bleed-out of preformed tape sealants.

1.2 The values stated in acceptable metric units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The subcommittee with jurisdiction is not aware of any similar ISO standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C717 Terminology of Building Seals and Sealants

D2203 Test Method for Staining from Sealants

E145 Specification for Gravity-Convection and Forced-Ventilation Ovens

3. Terminology

3.1 *Definitions*—The definitions of the following terms used in this test method are found in Terminology C717: preformed tape sealant, sealant.

¹ This test method is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants and is the direct responsibility of Subcommittee C24.20 on General Test Methods.

Current edition approved May 1, 2019. Published May 2019. Originally approved in 1974. Last previous edition approved in 2014 as C772 – 03(2014). DOI: 10.1520/C0772-03R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Summary of Test Method

4.1 The preformed tape sealant to be tested is placed on filter paper. The specimen is heat aged and examined for migration into the filter paper.

5. Significance and Use

5.1 Preformed tape sealants are tacky, deformable solids that are used under compression between two substrates in a variety of sealing applications. In general, oil migration or plasticizer bleed-out is not desirable. However, in some limited instances, a controlled amount of plasticizer migration is sometimes desired in order to improve the penetration of the tape into the interstices of porous substrates. This test method is designed to indicate whether or not a preformed tape sealant exhibits oil or plasticizer migration and, if so, to what extent.

6. Apparatus

6.1 *Vented Air Circulating Oven*, that complies with Specification E145 and is capable of aging samples at $70 \pm 2^\circ\text{C}$ ($158 \pm 3.6^\circ\text{F}$) or $100 \pm 2^\circ\text{C}$ ($212 \pm 3.6^\circ\text{F}$).

6.2 *Filter Paper*,³ six sheets, high-grade, rapid, 76 mm (3 in.) in diameter.

6.3 *Weight*, 1 kg (2.2 lb).

7. Sampling

7.1 Select a fresh roll of preformed tape sealant at least 13 mm (0.5 in.) wide and 3 mm (0.125 in.) thick. Remove a section of preformed tape sealant approximately 61 cm (2 ft) long from the roll and discard it.

8. Test Specimens

8.1 Prepare duplicate test specimens by cutting short lengths of preformed tape sealant with the release paper still in place and plying them together to form a solid pad having the

³ This test method was based on the use of Whatman No. 1 filter paper. The sole source of supply of the apparatus known to the committee at this time is Whatman Inc., 9 Bridewell Place, Clifton, NJ 07014. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

minimum surface dimensions of 38 mm (1.5 in.) by 38 mm and 3 mm (0.125 in.) thick.

8.2 Place each pad of preformed tape sealant on a piece of filter paper with the release paper side up.

8.3 Ensure adequate contact between the preformed tape sealant and the filter paper on each specimen by placing the 1-kg (2.2-lb) weight on top of the preformed tape sealant for 5 s.

9. Procedure

9.1 Place two additional pieces of filter paper under each of these test specimens.

9.2 Place each of these tape-filter paper assemblies in an air circulating oven maintained at $70 \pm 2^{\circ}\text{C}$ ($158 \pm 3.6^{\circ}\text{F}$) and condition them for 3 weeks at this temperature. (Alternatively, samples can be conditioned for 1 week at $100 \pm 2^{\circ}\text{C}$ ($212 \pm 3.6^{\circ}\text{F}$).

9.3 Examine the filter papers under each specimen for evidence of oil migration or plasticizer bleed-out as soon as possible after removal from the oven. The filter paper should be viewed from the back side when held up to a light.

10. Report

10.1 Report the following information:

10.1.1 Identification of the preformed tape sealant, that is, the name, lot number, and any other identifying characteristics.

10.1.2 Oven aging conditions used for this test.

10.1.3 For each specimen, number of filter papers stained or that show evidence of oil migration.

10.1.4 For each specimen, to the nearest 0.3 mm (0.01 in.) the average distance of the stain from the edge of the pad of tape on the filter paper that was in direct contact with the pad of tape compound.

10.1.5 For each specimen, whether there is any evidence of stain, oil migration, or plasticizer bleed-out on the first filter paper directly under the pad of tape compound.

NOTE 1—Care should be taken not to confuse the changes in filter paper color or opacity due to being in direct contact with the tape with evidence of oil migration or plasticizer bleed-out.

10.2 A stain index can be determined for any one specimen by adding the average distance of the stain and the number of filter papers stained. (See Test Method [D2203](#).)

11. Precision and Bias

11.1 Two round robins were conducted using this procedure and a variation wherein ultraviolet lights were also used as a heat source. Different laboratories showed excellent comparative results when ranking the relative oil migration of tape samples using this type of procedure.

12. Keywords

12.1 oil migration; plasticizer bleed; preformed tape sealants; tapes; tape sealants

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>