



Designation: C788 – 03 (Reapproved 2021)

Standard Specification for Nuclear-Grade Uranyl Nitrate Solution or Crystals¹

This standard is issued under the fixed designation C788; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification applies to nuclear-grade aqueous uranyl nitrate solution or crystals not exceeding 5 % ²³⁵U intended for subsequent manufacture into either UF₆ (for feed to an enrichment plant) or direct conversion to uranium oxide (for use in reactors).

1.2 This specification is intended to provide the nuclear industry with a general standard for aqueous uranyl nitrate solution or crystals. It recognizes the diversity of manufacturing methods and the processes to which it is subsequently to be subjected. It is therefore anticipated that it may be necessary to include supplementary specification limits by agreement between purchaser and manufacturer. Different limits are appropriate depending on whether or not the uranyl nitrate is to be converted to UF₆ for subsequent processing.

1.3 The purpose of this specification is: (a) to define the impurity and uranium isotope limits for commercial standard uranyl nitrate, and (b) to define additional limits for reprocessed uranyl nitrate (or any mixture of reprocessed and commercial standard uranyl nitrate). For such uranyl nitrates, special provisions may need to be made to ensure that no extra hazard arises to the employees, the process equipment, or the environment.

1.4 The scope of this specification does not comprehensively cover all provisions for preventing criticality accidents, for health and safety, or for shipping. Observance of this standard does not relieve the user of the obligation to conform to all international, federal, state and local regulations for processing, shipping, or any other way of using the uranyl nitrate. An example of a U.S. Government Document is the Code of Federal Regulations, Title 10, Part 50 (latest edition).

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the*

responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[C787 Specification for Uranium Hexafluoride for Enrichment](#)

[C799 Test Methods for Chemical, Mass Spectrometric, Spectrochemical, Nuclear, and Radiochemical Analysis of Nuclear-Grade Uranyl Nitrate Solutions](#)

[C859 Terminology Relating to Nuclear Materials](#)

[C996 Specification for Uranium Hexafluoride Enriched to Less Than 5 % ²³⁵U](#)

[C1233 Practice for Determining Equivalent Boron Contents of Nuclear Materials](#)

[C1295 Test Method for Gamma Energy Emission from Fission and Decay Products in Uranium Hexafluoride and Uranyl Nitrate Solution](#)

2.2 ANSI Standard:³

[ANSI/ASME NQA-1 Quality Assurance, Requirements for Nuclear Facility Applications](#)

2.3 U.S. Government Document:⁴

[Code of Federal Regulations, Title 10, \(Energy\), Part 50, Domestic Licensing of Production and Utilization Facilities](#)

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁴ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

¹ This specification is under the jurisdiction of ASTM Committee C26 on Nuclear Fuel Cycle and is the direct responsibility of Subcommittee C26.02 on Fuel and Fertile Material Specifications.

Current edition approved Oct. 1, 2021. Published October 2021. Originally approved in 1976. Last previous edition approved in 2015 as C788 – 03 (2015). DOI: 10.1520/C0788-03R21.

3.1.1 Terms shall be defined in accordance with Terminology C859, except for the following:

3.1.1.1 *commercial standard uranyl nitrate*—refers to uranyl nitrate made from unirradiated uranium. However, it is recognized that some contamination with reprocessed uranium may occur during routine processing; this is acceptable, provided that the product meets the specification for commercial standard uranyl nitrate as defined in 4.2.

3.1.1.2 *reprocessed uranyl nitrate*—refers to any uranyl nitrate made from uranium that has been exposed in a neutron irradiation facility and subsequently chemically separated from the fission products and transuranic isotopes so generated. The limits given in this specification are intended to be typical of reprocessed spent fuel having achieved burn-up levels of up to 50 000 megawatt day per ton of uranium in light water reactors and cooling for 10 years after discharge. It is recognized that different values would be necessary to accommodate different fuel histories.

4. Radionuclide Content

4.1 The ²³⁵U content shall be reported as g/100 g U.

4.2 For commercial standard uranyl nitrate, the concentration of ⁹⁹Tc, ²³²U, ²³⁴U and ²³⁶U shall be as specified in Specifications C787 or C996, as appropriate, unless otherwise agreed upon between purchaser and manufacturer. For ⁹⁹Tc and ²³²U, the specific isotopic measurements required by the appropriate specification may be waived, provided that the manufacturer can demonstrate compliance, for instance, through the manufacturer’s quality assurance records.

4.3 For reprocessed uranyl nitrate, the concentrations of ⁹⁹Tc, ²³²U, ²³⁴U and ²³⁶U shall be as specified in Specifications C787 or C996, as appropriate, unless otherwise agreed between purchaser and manufacturer.

4.4 For reprocessed uranyl nitrate, the total of the products of each specific mean gamma decay rate multiplied by each specific mean gamma energy per disintegration arising from fission products shall not exceed 3 × 10⁵ MeV-Bq/ Kg U. The radionuclides to be determined by the gamma spectrometer method of Methods C799, C1295, or equivalent.

4.5 For reprocessed uranyl nitrate that is to be converted to UF₆, the maximum alpha activity due to transuranic alpha emitters shall be 250 Bq/g U (15 000 dpm/g U); the maximum alpha activity due to neptunium shall be 125 Bq/g U (7500 dpm/g U). For reprocessed uranyl nitrate that is to be converted directly into UO₂ fuel, the transuranic alpha emitter specification limits of Specification C996 shall apply unless otherwise agreed upon between purchaser and manufacturer.

5. Chemical Requirements

5.1 The limits of uranium concentration and the free nitric acid concentration of the aqueous uranyl nitrate solution shall be agreed between purchaser and manufacturer.

5.2 The uranyl nitrate solution shall contain no more than 0.5 volume% of entrained organic materials.

5.3 When the uranyl nitrate is intended as feed material for conversion to uranium hexafluoride, the following shall apply:

5.3.1 The impurity limit of each element listed in Table 1 shall not exceed its designated maximum.

5.3.2 The sum of concentrations of the following elements (which do not form volatile fluorides) shall not exceed 500 µg/g U:

Aluminum	Iron	Silver
Barium	Lead	Sodium
Bismuth	Lithium	Strontium
Cadmium	Magnesium	Thorium
Calcium	Manganese	Tin
Copper	Nickel	Zinc
	Potassium	Zirconium

5.4 When the uranyl nitrate is intended for direct conversion to an oxide (not through the hexafluoride), the following clauses shall apply:

5.4.1 The impurity limit of each element listed in Table 2 shall not exceed its designated maximum. The total of all elements listed in this table shall not exceed 1500 µg/g of uranium.

5.4.2 The total equivalent boron content (EBC) shall not exceed 4.0 µg/g U. The total EBC shall be determined per Practice C1233. For fast reactor use the limitation on EBC does not apply.

5.5 If the concentrations of any of the elements used in the calculations in 5.3 and 5.4 are reported as a “less than” value, this “less than” value shall be used for any further calculations involving the concentration of this element.

6. Sampling

6.1 A representative sample of sufficient size to perform the tests prescribed herein shall be taken. Because of the potential presence of several liquid phases (organic materials), careful attention should be taken when sampling and subsampling.

6.2 Because of the potential presence of several liquid phases (organic materials) in uranyl nitrate solution, careful attention should be taken when sampling and subsampling.

6.3 Uranyl nitrate crystals are hygroscopic and retain sufficient water after exposure to a moist atmosphere to cause detectable errors. Sample, weigh, and handle the sample under conditions that will ensure that the sample is representative of

TABLE 1 Impurity Limits in Uranyl Nitrate for Conversion to Uranium Hexafluoride

Element	Maximum Concentration Limit, µg/g U
Antimony	1
Arsenic	3
Boron	1
Bromine	5
Chlorine	100
Chromium	10
Fluorine	25
Molybdenum	1.4
Niobium	1
Phosphorus	50
Ruthenium	1
Silicon	100
Sulphur	400
Tantalum	1
Titanium	1
Tungsten	1.4
Vanadium	1.4

TABLE 2 Impurity Limits in Uranyl Nitrate for Direct Conversion to Oxide

Element	Maximum Concentration Limit, µg/g U
Aluminum	150
Calcium + Magnesium	150
Chlorine + Fluorine	350
Chromium	150
Cobalt	80
Copper	200
Iron	200
Lead	200
Manganese	200
Molybdenum	200
Nickel	150
Phosphorus	200
Silicon	200
Tantalum	200
Thorium	10
Tin	200
Titanium	200
Tungsten	200
Vanadium	200
Zinc	200

the lot. Analytical confirmation of sampling plans shall be documented as part of the manufacturer’s quality assurance and nuclear materials control and accountability programs.

6.4 All samples shall be clearly identified, including the manufacturer’s lot number.

6.5 All containers used for a lot shall be positively identified as containing material from a particular homogeneous lot.

7. Methods of Chemical and Isotopic Analysis

7.1 Methods **C799**, or demonstrated equivalent, shall be used as mutually agreed between the purchaser and manufac-

turers. Methods not currently provided by Methods **C799** shall be as mutually agreed between purchaser and manufacturers.

8. Quality Assurance

8.1 Quality assurance requirements shall be agreed upon between the purchaser and manufacturer when specified in the purchase order. Code of Federal Regulations, Title 10, Part 50, Appendix B and ASME NQA-1 are referenced as guides.

9. Keywords

9.1 uranium isotope limits; uranium solutions; uranyl nitrate

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/