



Designation: D7050 – 04 (Reapproved 2019)

## Standard Practice for Rubber from Natural Sources—Sampling and Sorting Bales Based on Predicted Processing Properties<sup>1</sup>

This standard is issued under the fixed designation D7050; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This practice covers the sorting of natural rubber bales of TSR10 or TSR20 in the factory according to their predicted processing performance based on differences in viscoelastic properties.

1.2 This practice determines which bales should be used in factory compounds which benefit from using “soft” natural rubber versus which work better with “hard” natural rubber.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D1485 Practice for Rubber from Natural Sources—Sampling and Sample Preparation](#)

[D2227 Specification for Natural Rubber \(NR\) Technical Grades](#)

[D3194 Test Method for Rubber From Natural Sources—Plasticity Retention Index \(PRI\)](#)

[D6204 Test Method for Rubber—Measurement of Unvulcanized Rheological Properties Using Rotorless Shear Rheometers](#)

### 3. Significance and Use

3.1 In accordance with Specification [D2227](#), shipments of TSR10 and TSR20 must meet a minimum initial Wallace plasticity ( $P_o$ ) of 30 to be accepted. However, even with this minimum restriction, the uncured viscoelastic or “processabil-

ity” properties are allowed to vary greatly. This variation in properties can significantly affect the quality and efficiency of a factory operation.

3.2 Bales of TSR10 or TSR20 which are lower in their uncured elastic quality (“soft” rubber) in some cases may impart better processing properties to tire innerliners, cushion gums, and sidewalls. “Soft” bales sometimes impart better building tack, better mold flow, and lower extrusion die swell with better dimensional stability. Also, these “soft” rubber bales may dissolve faster in solvents for adhesion dipping.

3.3 Bales of TSR10 or TSR20 that are higher in their uncured elastic quality (“hard” rubber) in some cases generate greater shearing during the initial stages of a factory mix, which result in a faster breakdown and a shorter mix cycle.

3.4 Therefore, in a factory operation, sometimes segregating TSR10 or TSR20 shipments into “soft” and “hard” categories can improve the efficiency and quality of a factory operation.

### 4. Sampling

4.1 *Sample Size*—The number of samples to be selected to represent the lot may be determined by the size of the lot as indicated in Practice [D1485](#), Table 1.

4.2 Alternatively, five bales from a 36-bale pallet may be sampled.

4.3 Samples from these bales should be taken from within the bale, not from the edges, because bale surface exposure to the air will cause surface samples to not be representative of the rubber inside the bale.

### 5. Lot Sorting

5.1 The criteria for sorting should be based on a repeatable measure of uncured elasticity of the raw natural rubber.

5.2 Measuring uncured elastic modulus  $G'$  at 1 Hz, 100 % strain, 100°C in accordance with Test Method [D6204](#), Part B, has been found to be an effective method for segregating “soft” natural rubber from “hard” natural rubber used in production. See also Test Method [D3194](#).

5.3 The segregating elastic modulus value  $G'_{SEG}$  is established as the criteria for separating “soft” natural rubber from “hard” natural rubber as shown in [Fig. 1](#).

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee [D11](#) on Rubber and Rubber-like Materials and is the direct responsibility of Subcommittee [D11.22](#) on Natural Rubber.

Current edition approved May 1, 2019. Published June 2019. Originally approved in 2004. Last previous edition approved in 2014 as D7050 – 04 (2014). DOI: 10.1520/D7050-04R19.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.




FIG. 1 Segregating Raw Natural Rubber Shipments of TSR10 or TSR20 for Factory Production

5.4 The value assigned to  $G'_{SEG}$  will depend on the factory setting. It will be dependent on the type of different compounds being mixed. A value must be assigned that will provide the best balance for quality and cost effectiveness for each production plant site.

## 6. Keywords

6.1 hard rubber; natural rubber; processability; processing properties; sampling; soft rubber; sorting bales

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*