



Designation: D763 – 06 (Reapproved 2019)

Standard Specification for Raw and Burnt Umber Pigments¹

This standard is issued under the fixed designation D763; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the pigments commercially known as raw umber and burnt umber.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D50 Test Methods for Chemical Analysis of Yellow, Orange, Red, and Brown Pigments Containing Iron and Manganese

D185 Test Methods for Coarse Particles in Pigments

D280 Test Methods for Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments

D387 Test Method for Color and Strength of Chromatic Pigments with a Mechanical Muller

D1208 Test Methods for Common Properties of Certain Pigments

3. Composition and Properties

3.1 *Dry Pigments*—The pigments shall conform to the following requirements:

3.1.1 *Raw Umber*—The pigment shall be in a soft, dry form and shall be a hydrated oxide of iron (together with such manganese that is naturally associated with it) permeating a siliceous base and shall be free of admixtures of other

substances except carbon pigments. The pigment shall conform to the requirements for composition prescribed in **Table 1**.

3.1.2 *Burnt Umber*—The pigment shall be produced by the calcination of raw umber and shall be free of admixtures of other substances except carbon pigments. The pigment shall conform to the requirements for composition prescribed in **Table 1**.

3.2 *Paste in Oil*—For both raw and burnt umber, the paste in oil shall be made by thoroughly grinding the pigment with linseed oil (with or without a small amount of volatile thinner) together with (where necessary) small amounts of wetting or dispersing agents to produce a paste or semipaste of satisfactory consistency. As received, it shall not be caked in the container and shall break up readily in linseed oil to form a smooth paint of brushing consistency. It shall mix readily in all proportions, without curdling, with linseed oil, turpentine, or volatile petroleum spirits, or any mixture of these substances. The paste shall conform to the following requirements:

Pigment, min, %	55
Nonvolatile vehicle, min, %	80
Moisture by distillation, max, %	2.0
Coarse particles and skins (total residue retained on a No. 325 (45- μ m sieve), max, % of dry pigment	1.0

3.3 The mass color and character of the tint and the tinting strength formed by a mixture with a white pigment shall be within mutually agreed upon limits of a standard acceptable to both the purchaser and the seller.

4. Sampling

4.1 Two samples shall be taken at random from different packages from each lot, batch, day's pack, or other unit of production in a shipment. When no markings distinguishing between units of production appear, samples shall be taken from different packages in the ratio of two samples for each 4540 kg or 10 000 lb, except that for shipments of less than 10 000 lb, two samples shall be taken. At the option of the purchaser, the samples may be tested separately or after blending in equal quantities the samples from the same production unit to form a composite sample.

5. Test Methods

5.1 Tests shall be conducted in accordance with the following ASTM test methods. Test procedures not covered by ASTM test methods shall be mutually agreed upon by the purchaser and the seller.

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved June 1, 2019. Published June 2019. Originally approved in 1944. Last previous edition approved in 2012 as D763 – 06 (2012). DOI: 10.1520/D0763-06R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**TABLE 1 Requirements for Composition of Raw and Burnt Umber Pigments**

	Raw Umber	Burnt Umber
Iron oxide (Fe ₂ O ₃), min, %	37	42
Calcium compounds (as CaO), max, %	5.0	5.0
Moisture and other volatile matter, max, %	5.0	5.0
Coarse particles (total residue retained on a No. 325 (45-μm) sieve), max, %	2.0	2.0
Organic colors, max, %	none	none

5.3 *Moisture in Paste in Oil*—Test Methods D280, except that the sample shall be weighed instead of measured and the results shall be expressed as weight percentage instead of volume.

5.4 *Coarse Particles*—Test Methods D185.

5.5 *Pigment and Linseed Oil in Paste in Oil*—Test Methods D1208.

5.6 *Mass Color and Tinting Strength*—Test Method D387.

6. Keywords

5.2 *Chemical Analysis of Dry Pigment*—Test Methods D50.

6.1 hydrated; pigment; raw and burnt umber

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>