



Designation: A942/A942M – 95 (Reapproved 2018)

# Standard Specification for Centrifugally Cast White Iron/Gray Iron Dual Metal Abrasion- Resistant Roll Shells<sup>1</sup>

This standard is issued under the fixed designation A942/A942M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers double pour, centrifugally cast, abrasion-resistant roll shells for general application. The outer layer is white iron and the inner layer is gray iron. There shall be no gradient of mottled iron between the white iron and the gray iron.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.2.1 Within the text, the SI units are shown in brackets.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

A48/A48M Specification for Gray Iron Castings

E8/E8M Test Methods for Tension Testing of Metallic Materials

E10 Test Method for Brinell Hardness of Metallic Materials

## 3. Classification

3.1 The white iron portion of the casting shall be classified by type based upon Brinell hardness.

3.2 The gray iron portion of the casting shall be classified by class based upon tensile strength.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A04 on Iron Castings and is the direct responsibility of Subcommittee A04.01 on Grey and White Iron Castings.

Current edition approved Nov. 1, 2018. Published November 2018. Originally approved in 1995. Last previous edition approved in 2012 as A942 – 95 (2012). DOI: 10.1520/A0942-95R18.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 4. Ordering Information

4.1 Orders for material to this specification shall include the following:

- 4.1.1 Specification title, designation, and year of issue,
- 4.1.2 Quantity of castings required,
- 4.1.3 Required dimensions and thickness of white iron layer (8.1),
- 4.1.4 Surface condition—as cast or machined,
- 4.1.5 Type of white iron required for the outer layer of the casting (7.1),
- 4.1.6 Class of gray iron required for the inner layer (7.2),
- 4.1.7 Certification, if required (Section 13), and
- 4.1.8 Special position of marking information, if required (Section 14).

4.2 Additional requirements may be agreed upon between the manufacturer and the purchaser.

## 5. Materials and Manufacture

5.1 Both the white and the gray irons may be melted by any suitable melting process.

5.2 The white iron portion of the casting shall be produced by chemistry rather than chilling.

## 6. Chemical Composition

6.1 A chemical analysis shall be performed by the manufacturer on both the white and gray irons. The chemical compositions shall be controlled to obtain the required mechanical properties.

## 7. Mechanical Properties

7.1 The white iron shall conform to the following requirements:

Type I – 450 to 500 HB  
Type II – 500 to 550 HB  
Type III – 550 to 600 HB  
Type IV – 600 to 650 HB

7.2 The gray iron shall conform to the following requirements:

| Class  | Tensile Strength |            |
|--------|------------------|------------|
|        | min, ksi         | min, [MPa] |
| No. 20 | 20               | [138]      |
| No. 25 | 25               | [172]      |
| No. 30 | 30               | [207]      |
| No. 35 | 35               | [241]      |





## **8. Other Requirements**

8.1 The thickness of the white iron layer shall be a minimum of 1/2 in.

8.1.1 The thickness of the white iron layer shall be measured on the roll face at each end and shall conform to the specified thickness.

## **9. Finish and Appearance**

9.1 All exterior surfaces shall be machined or ground prior to the rolls being placed into service.

9.2 The manufacturer shall be responsible for providing castings with adequate stock for final machining.

9.3 Surfaces and corners of the machined castings shall be free from burrs and extremely sharp edges.

9.4 Machined surfaces of the castings may be protected by the application of a rust and corrosion-preventive coating.

## **10. Sampling**

10.1 Each casting shall be tested for chemical composition, hardness, and tensile strength.

10.2 The white iron hardness shall be determined on crop ends removed from the casting.

10.3 The tension test of the gray iron shall be performed on specimens obtained from separately cast test bars poured in accordance with Specification **A48/A48M**. Standard test bar B shall be the size of the test bar poured.

10.4 Chemical analysis shall be performed on samples obtained during pouring of the iron.

## **11. Test Methods**

11.1 The hardness test shall be performed in accordance with Test Method **E10**, using a 10-mm tungsten carbide ball and 3000-kgf load. Test results shall be considered accurate up to 700 HB.

11.2 The tension test shall be performed in accordance with Test Methods **E8/E8M**.

## **12. Inspection**

12.1 All tests and inspections required by this specification shall be performed by the manufacturer or other reliable source whose services have been contracted by the manufacturer. Complete records of all tests and inspections shall be maintained by the manufacturer, and shall be available for review by the purchaser.

## **13. Certification**

13.1 When specified by the purchaser, the manufacturer's certification shall be furnished to the purchaser stating that the material was manufactured, sampled, tested, and inspected in accordance with this specification. This certification shall include the results of all tests required by this specification and give the thickness of the white iron supplied.

## **14. Packaging and Package Marking**

14.1 When specified by the purchaser, the manufacturer's name or identifying mark shall be stamped at one end in the gray iron portion of the casting. When further specified, the casting identification number shall be stamped at the casting end.

14.2 Unless otherwise specified by the contract or purchase order, castings shall be packed in accordance with the manufacturer's commercial practice to ensure acceptance and safe delivery by the carrier.

## **15. Keywords**

15.1 abrasion-resistant; cast iron; centrifugal casting; dual metal; gray cast iron; roll shell; white cast iron

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*