



Designation: A997 – 08 (Reapproved 2018)

Standard Practice for Investment Castings, Surface Acceptance Standards, Visual Examination¹

This standard is issued under the fixed designation A997; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (^ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the acceptance criteria for surface inspection of investment castings by visual examination.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Terminology

2.1 Definitions of Terms Specific to This Standard:

2.1.1 *linear discontinuity, n*—a discontinuity whose length is equal to or greater than three times its width. Cracks and cold shuts are examples of linear discontinuity.

¹ This practice is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved March 1, 2018. Published March 2018. Originally approved in 1998. Last previous edition approved in 2012 as A997 – 08 (2012). DOI: 10.1520/A0997-08R18.

2.1.2 *positive metal, n*—raised metal on the casting surface, usually associated with the breakdown of the mold and its replacement with the casting metal.

2.1.3 *surface pit, n*—a nonlinear depression in the cast surface whose length is less than three times its width. Surface pits may be the result of gas or non-metallic inclusions.

2.1.4 *surface roughness, n*—a measure of surface texture, usually determined by the use of a comparator.

3. Ordering Information

3.1 The inquiry or order should specify the following information:

3.1.1 *Acceptance Level*—More than one acceptance level may be specified for different surfaces of the same casting (see Section 4),

3.1.2 If any types of discontinuities are unacceptable,

3.1.3 Casting surfaces to be examined,

3.1.4 Number of castings to be examined, and

3.1.5 Additional acceptance criteria as applicable to all or portions of the casting surface.

4. Acceptance Criteria

4.1 Levels of acceptance for visual inspection are listed in **Table 1**.

4.2 Parts shall not exhibit any linear discontinuities.

4.3 Surface roughness and surface pits that will be removed by machining are considered acceptable.

4.4 Surface discontinuities not covered in this practice shall be a matter of agreement between the purchaser and the manufacturer.

TABLE 1 Visual Inspection Acceptance Criteria ^{A,B}

| Surface Feature | Level II | Level III | Level IV |
|---|---|---|--|
| Surface Pits ^{C,D,E} | 0.030 in. (0.76 mm) diameter by 0.015 in. (0.38 mm) deep with no more than 1 per in. (645 ² mm) | 0.060 in. (1.52 mm) diameter by 0.030 in. (0.76 mm) deep with no more than 1 per in. (645 ² mm) | 0.060 in. (1.52 mm) diameter by 0.030 in. (0.76 mm) deep with no more than 4 per in. (645 ² mm)† |
| Positive Metal ^{D,E} | 0.060 in. (1.52 mm) diameter by 0.015 in. (0.38 mm) high with no more than 1 per in. (645 ² mm) | 0.125 in. (3.18 mm) diameter by 0.030 in. (0.76 mm) high with no more than 1 per in. (645 ² mm) | 0.125 in. (3.18 mm) diameter by 0.030 in. (0.76 mm) high with no more than 4 per in. (645 ² mm) |
| Parting Line and Ejector Pin Marks Height or Depth ^C | 0.005 in. (0.13 mm) | 0.010 in. (0.25 mm) | 0.020 in. (0.51 mm) |
| Gate Height ^F | 0.015 in. (0.38 mm) | 0.030 in. (0.76 mm) | 0.045 in. (1.14 mm) |
| Surface Roughness ^E | 100 μin. (2.5 μm) | 125 μin. (3.2 μm) | 200 μin. (5.0 μm) |

^A Features in excess of those specified in the table are not acceptable.

^B Level I criteria may be established in the future depending on need. Maximum

^C surface pit, parting line, and ejector pin mark depth shall not violate drawing minimum wall thickness.

^D Surface pits or positive metal less than 0.010 in. (0.25 mm) diameter and less than 0.010 in. (0.25 mm) deep or high shall be considered non-relevant.

^E Determined by comparator or tactile source.

^F Machined and non-machined surfaces †Value was editorially corrected in June 2006.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>