



Designation: B739 – 03 (Reapproved 2018)

Standard Specification for Nickel-Iron-Chromium-Silicon Alloy Welded Tube¹

This standard is issued under the fixed designation B739; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers alloys UNS N08330 and UNS N08332 in the form of welded tube intended for heat resisting applications and general corrosive service.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

B536 Specification for Nickel-Iron-Chromium-Silicon Alloys (UNS N08330 and N08332) Plate, Sheet, and Strip

B751 Specification for General Requirements for Nickel and Nickel Alloy Welded Tube

3. General Requirement

3.1 Material furnished under this specification shall conform to the applicable requirements of Specification **B751** unless otherwise provided herein.

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Nov. 1, 2018. Published November 2018. Originally approved in 1985. Last previous edition approved in 2013 as B739 – 03 (2013). DOI: 10.1520/B0739-03R18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

4.1.1 Alloy (**Table 1**),

4.1.2 ASTM designation and year of issue,

4.1.3 Dimensions (outside or inside diameter and nominal wall thickness),

4.1.4 Length (specific or random),

4.1.5 Quantity (feet or number of pieces),

4.1.6 *Certification*—State if certification is required,

4.1.7 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished, and

4.1.8 *Purchaser Inspection*—If purchaser wishes to witness tests or inspection of material at place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed.

5. Materials and Manufacture

5.1 The tube shall be made from flat-rolled alloy conforming to Specification **B536**, by an automatic welding process with no addition of filler metal. Subsequent to welding and prior to final heat treatment, the tube shall be cold-worked either in both weld and base metal or in weld metal only.

6. Chemical Composition

6.1 The material shall conform to the requirements, as to chemical composition specified in **Table 2**.

6.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations per Specification **B751**.

7. Mechanical Properties and Other Requirements

7.1 The tensile properties of the material at room temperature shall conform to those shown in **Table 1**.

7.2 *Grain Size*—Annealed Alloy UNS N08332 shall conform to an average grain size of ASTM No. 5 or coarser.

7.3 *Annealing Temperature*—Alloy UNS N08330 shall be annealed at 1900°F (1040°C) minimum. Alloy UNS N08332 shall be annealed at 2050°F (1120°C) minimum.

TABLE 1 Mechanical Properties

Alloy	Condition	Tensile Strength, min, psi (MPa)	Yield Strength, 0.2 % offset, min, psi (MPa)	Elongation in 2 in. or 50 mm, or 4D, min,%	Hardness ^A
UNS N08330	Annealed	70 000 (483)	30 000 (207)	30	70–90 HRB
UNS N08332	Annealed	67 000 (462)	27 000 (186)	30	65–88 HRB

^A Hardness values are informative only and not to be construed as the basis for acceptance.

TABLE 2 Chemical Requirements

Element	Composition Limits, %
Carbon	... ^A
Manganese	2.00 max
Phosphorus	0.03 max
Sulfur	0.03 max
Silicon	0.75–1.50
Chromium	17.0–20.0
Nickel	34.0–37.0
Copper	1.00 max
Lead	0.005 max
Tin	0.025 max
Iron	remainder ^B

^A Alloy UNS N08330: 0.08 max.

Alloy UNS N08332: 0.05–0.10.

^B Element shall be determined arithmetically by difference.

8. Keywords

8.1 welded tube; N08330; N08332

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/