



Designation: B858 – 06 (Reapproved 2018)

Standard Test Method for Ammonia Vapor Test for Determining Susceptibility to Stress Corrosion Cracking in Copper Alloys¹

This standard is issued under the fixed designation B858; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes a procedure to determine the presence of residual stresses in wrought copper alloy products that may lead to stress corrosion cracking. An ammonia vapor atmosphere is used as an accelerated test.

1.2 This test method is only suitable for products fabricated from copper alloys that are known to be susceptible to stress corrosion cracking in ammonia vapor atmospheres. It is intended to create an environmental condition of reproducible severity.

NOTE 1—It is well known that the critical step in the cracking mechanism is the development of an environment in the condensate film that occurs on the surface of the test specimen, and is rich in copper complex ions.

1.3 The severity of this test method depends upon the pH of the corrosive solution. In [Annex A1](#) are given four different atmospheres to which the product may be exposed, and the appropriate pH of the solution to be used for the test, depending on the risk level associated with the intended application.

1.3.1 The appropriate pH value for the test shall be specified in the product specification, or as per established agreement between the supplier and purchaser, with respect to the alloy and its intended application.

1.4 *Units*—The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the*

Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 *ASTM Standards:*²

[B154](#) Test Method for Mercurous Nitrate Test for Copper Alloys

[B846](#) Terminology for Copper and Copper Alloys

[D1193](#) Specification for Reagent Water

3. Terminology

3.1 For definitions of terms related to copper and copper alloys, refer to Terminology [B846](#).

3.2 *Definitions:*

3.2.1 *applied stress, n*—stress in a body as a result of application of an external load.

4. Summary of Test Method

4.1 The prepared test specimen is placed in a closed container and exposed to ammonia vapor with a specific pH at ambient temperature for 24 h. Upon removal from the test atmosphere, the test specimen is examined for the presence of cracks.

5. Significance and Use

5.1 This test method is an accelerated test to determine if a copper alloy product will be susceptible to stress-corrosion cracking when exposed to a particular atmospheric condition during service with the appropriate risk level—see [Annex A1](#).

5.1.1 This test method is generally intended to determine if a copper alloy product will crack because of internal stresses when subjected to the test, and is not intended for testing assemblies under applied stress. If used for this purpose, it shall be for information only and not a cause for rejection of the assembly, its component parts, or the original mill product.

¹ This test method is under the jurisdiction of ASTM Committee [B05](#) on Copper and Copper Alloys and is the direct responsibility of Subcommittee [B05.06](#) on Methods of Test.

Current edition approved March 1, 2018. Published March 2018. Originally approved in 1995. Last previous edition approved in 2012 as B858 – 06 (2012). DOI: 10.1520/B0858-06R18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

6. Apparatus

6.1 *pH meter*.

6.2 *Closed vessel*, such as a desiccator.

6.3 Equipment for examining test pieces at 10× to 15× magnification.

7. Reagents and Materials

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type IV or better, of Specification D1193.

7.3 *Ammonium Chloride Solution (4N)*—Dissolve 107 g of ammonium chloride (NH_4Cl) in water and dilute to 500 mL. Store the solution in a closed vessel.

7.4 *Hydrogen Peroxide (H_2O_2)*, 30 to 35 % technical grade. (**Warning**—Hydrogen peroxide in high concentrations can cause severe skin burns. Use of proper safety equipment is advised.)

7.5 *Sodium Hydroxide Solution (300 to 500 g/L)*—Dissolve 300 to 500 g of sodium hydroxide (NaOH) into water and dilute to 1 L. (**Warning**—Sodium hydroxide can cause chemical burns to the skin and eyes. Use of proper safety equipment is advised.)

7.6 A clean organic solvent or hot alkaline solution that contains no ammoniacal-type groups or substituents.

7.7 *Sulfuric Acid Solution (50 mL/L)*—Slowly add 50 mL of concentrated sulfuric acid (H_2SO_4) into water and dilute to 1 L.

8. Test Media

8.1 Slowly add the sodium hydroxide solution to the ammonium chloride solution to give a test solution with a pH value appropriate for the intended application (see Annex A1). Maintain the solution at ambient temperature and dilute with DI water up to a volume of 1 L. Check the pH value with the pH meter after dilution. Prepare the solution preferably in a fume hood in a laboratory using appropriate safe laboratory procedures and store it in a closed vessel. Before use, check the pH value again, and adjust if necessary.

8.1.1 In the closed test vessel, the ratio of surface area of test solution to air volume of the vessel above the solution shall be a minimum of 20 cm^2/L .

8.2 The pickling solution for cleaning test pieces before and after testing shall be 5 % sulfuric acid. If necessary, for

cleaning test pieces after testing, a small amount of hydrogen peroxide solution may be added to the pickling solution (for example, 20 to 30 mL of hydrogen peroxide solution per litre of pickling solution).

9. Test Specimen Preparation

9.1 The test specimen size shall be prescribed in the specification of the product or part being tested. In the event that a test specimen size is not prescribed in a given rod, wire, or tube specification, a full cross section having a minimum length of 152 mm shall be tested.

9.2 The presence of burrs on the test specimen may contribute to acceleration of stress corrosion cracking if not removed before the ammonia vapor test. The burrs shall be removed by fine file or abrasive paper to facilitate this test.

9.3 Degrease the test specimen using the clean organic solvent or alkaline solution.

9.4 After degreasing, clean the test piece in the pickling solution and immediately thereafter thoroughly rinse it, first in cold running water, then in hot water, and finally, completely dry it in a stream of warm air.

10. Test Procedure

10.1 Allow the dry test piece to reach the exposure temperature specified below, and transfer it immediately to the closed vessel (see 6.2) at the same temperature, and containing the freshly prepared test solution at the specified pH value (see 8.1).

10.1.1 Suspend (or place) the test piece such that the ammonia vapor has free access to all surfaces, not less than 50 mm above the test solution surface.

10.1.1.1 When placed on a porcelain support within the test vessel, the region of the test piece within 5 mm of the support shall be disregarded when inspecting for cracks.

10.1.1.2 The test piece shall be placed no less than 10 mm from the inside walls of the test vessel.

10.1.1.3 When more than one test piece is placed in the vessel, the test pieces shall be no less than 10 mm apart.

10.2 The volume of the test solution shall be at least 200 mL per square decimeter of test piece surface. The exposure temperature shall be between 20 and 30 °C and shall be kept constant to within ± 1 °C during the test. In case of dispute, the exposure temperature shall be 25 ± 1 °C.

10.3 The exposure time shall be 24 h.

10.4 After exposure, remove the test piece from the closed vessel and immediately clean it in pickling solution for a few minutes at ambient temperature (below 40 °C), or until the surfaces of the test piece are sufficiently clean from corrosion products to allow observation of possible cracks. After rinsing in water and drying in warm air, examine the surface of the test piece for cracks at a magnification of 10 to 15×.

10.5 Before inspection, deform the test piece slightly by bending or flattening to open up fine cracks to make them more easily observable.

10.6 Metallographic examination may be used to evaluate the nature of any observed cracks.

³ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.



11. Test Report

- 11.1 The test report shall contain the following information:
- 11.1.1 Sample identification,
 - 11.1.2 Reference to the test method used,
 - 11.1.3 The pH value used for the solution producing the ammonia vapor atmosphere,
 - 11.1.4 The number of replicate test pieces tested,
 - 11.1.5 The test results: cracks or no cracks (as required in the appropriate product specification),
 - 11.1.6 Any other features of the material noted during the determination, and
 - 11.1.7 The date of the test.

12. Precision and Bias

- 12.1 No information is presented about either the precision or bias of this test method for determining susceptibility to stress corrosion cracking in copper alloys since the procedure is directed at a subjective nonquantitative visual interpretation of condition of the specimen and its relation to an applicable product specification.

13. Keywords

- 13.1 ammonia test; copper alloys; residual stress; stress corrosion; stress corrosion cracking

ANNEX

(Mandatory Information)

A1. REPRESENTATIVE pH VALUES

A1.1 On the basis of the known correlation between the behavior of test pieces in the ammonia vapor test and the behavior of copper alloy products under service conditions, the following pH values are considered as being representative of atmospheres of different corrosiveness and corresponding to different safety requirements.

A1.1.1 An appropriate risk level (pH value) shall be specified in the product specification.

Corrosiveness of Atmosphere	pH Value Safety Requirement	
	Low	High
Low		
Indoor atmosphere conditions	8.3	9.5
Moderate		
Indoor atmosphere with risk of formation of condensation	9.5	10.0
Outdoor atmosphere, temperate climate	9.8	10.0
High		
Atmosphere with ammoniacal pollution, for example in stables	10.0	10.5

APPENDIX

(Nonmandatory Information)

X1. RATIONALE (COMMENTARY)

X1.1 This test method was developed to address the demand for a test method for determination of the presence of residual stresses in copper alloy products which may lead to stress corrosion cracking other than the mercurous nitrate test, Test Method **B154**. Research work performed by Mattsson, et al⁴

validates the technical integrity of the test method.

X1.2 This test method does not attempt to compare the effectiveness of the test to other test methods, including the mercurous nitrate test, Test Method **B154**, nor does it attempt to quantify its relative effectiveness on various copper alloy products. These issues must be addressed on a case-by-case basis, since such products and tests are specific for their respective requirements and applications.

⁴ Einar Mattsson, Rolf Holm, and Lars Hassel, "Ammonia Test for Stress Corrosion of Copper Alloys."



B858 – 06 (2018)

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>