



Designation: B880 – 14 (Reapproved 2019)

Standard Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys¹

This standard is issued under the fixed designation B880; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers limits of variation for determining acceptability of the chemical composition of cast or wrought nickel, nickel alloy, and cobalt alloy parts and/or material supplied by a producer. Check analysis limits for elements or for ranges of elements not currently listed herein shall be as specified in the applicable material specification or as agreed upon by purchaser and supplier.

1.2 In case of any conflicting requirements, the requirements of the purchase order, the individual material specification, and this general specification shall prevail in the sequence named.

1.3 When specifically referenced in the material specification, the buyer may elect to apply check analysis limits to determine acceptability at his final acceptance or verification procedures. Check analysis limits are not permitted or are to be used by the producer for their own ladle or ingot analysis acceptance testing.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

¹ This specification is under the jurisdiction of Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved April 1, 2019. Published May 2019. Originally approved in 1998. Last previous edition approved in 2014 as B880 – 14. DOI: 10.1520/B0880-14R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[E55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition](#)

[E88 Practice for Sampling Nonferrous Metals and Alloys in Cast Form for Determination of Chemical Composition](#)

[E1473 Test Methods for Chemical Analysis of Nickel, Cobalt and High-Temperature Alloys](#)

2.2 SAE Standards:³

[AMS 2269 Chemical Check Analysis Limits Nickel, Nickel Alloys and Cobalt Alloys](#)

3. Terminology

3.1 Definitions:

3.1.1 *check (product or verification) analysis, n*—analysis made by buyer of parts and materials to verify conformity to specification, or to determine variations in compositions within a heat or lot.

3.1.1.1 *Discussion*—Heat or lot acceptance or rejection of parts and materials may be made by applying check limits as described in 3.1.2. Check limits of finished parts or material do not apply to elements whose percentage can be varied by fabricating techniques employed unless the sample is taken in such a manner as to exclude such variations.

3.1.2 *variation limit, under minimum or over maximum, n*—it is the amount of variation for a specified element, which may vary either under or over the specified composition limit during an individual check analysis.

3.1.2.1 *Discussion*—In no case shall the reported determinations of any element in a heat, using the same analytical procedure, vary both above and below the specified range.

3.1.3 *remainder or balance, n*—refers to main element, which forms the basis of that particular alloy and from which the alloy is made.

3.1.3.1 *Discussion*—It is assumed to be present in an amount approximately equal to the difference between 100 % and the sum percentage of the alloying elements and listed impurities or residual elements. It need not be analyzed or need an actual percentage figure for reporting purposes.

³ Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096, <http://www.sae.org>.

3.1.4 *residual elements, n*—specified or unspecified elements, not intentionally added, which may be present, due to their presence in starting raw materials or manufacturing processes.

3.1.4.1 *Discussion*—Producers will not normally analyze for such elements, unless specifically asked for in the specification or purchase order.

3.1.4.2 *Discussion*—Reporting analyses of unspecified elements is permitted.

3.1.5 *remainder or balance, n*—the element comprising the major portion of an alloy’s composition, determined by subtracting the sum of the amounts of all analyzed elements (specified elements, and when measured, unspecified elements) from 100 %.

3.1.5.1 *Discussion*—It is not the intention of 3.1.5 that an analysis is required for any unspecified element.

3.1.5.2 *Discussion*—A chemical analysis for the remainder or balance element is not required. The manufacturer is permitted to report the analysis of the element as “balance” or “remainder” and need not report the result of the actual arithmetic calculation, unless requested by the purchaser in the purchase order.

4. Technical Requirements

4.1 *Analytical Procedures*—Referee analysis shall be by any method acceptable to purchaser and vendor.

4.2 *Check Analysis Limits*—Shall be as shown in Table 1.

TABLE 1 Check Analysis Variation

Element	Limit or Maximum of Specified Element, %	Variation Under min or Over max
Carbon	Up to 0.02, incl	0.005
	Over 0.02 to 0.20, incl	0.01
	Over 0.20 to 0.60, incl	0.02
	Over 0.60 to 1.00, incl	0.03
Manganese	Up to 1.00, incl	0.03
	Over 1.00 to 3.00, incl	0.04
	Over 3.00 to 6.00, incl	0.07
	Over 6.00 to 10.00, incl	0.10
Silicon	Up to 0.05, incl	0.01
	Over 0.05 to 0.25, incl	0.02
	Over 0.25 to 0.50, incl	0.03
	Over 0.50 to 1.00, incl	0.05
	Over 1.00 to 4.50, incl	0.10
Phosphorus	All	0.005
Sulfur	Up to 0.02, incl	0.003
	Over 0.02 to 0.06, incl	0.005
Chromium	Up to 5.00, incl	0.10
	Over 5.00 to 15.00, incl	0.15
	Over 15.00 to 25.00, incl	0.25
	Over 25.00 to 35.00, incl	0.30
	Over 35.00 to 45.00, incl	0.40
	Over 45.00 to 50.00, incl	0.50
Nickel	Up to 1.00, incl	0.05
	Over 1.00 to 5.00, incl	0.10
	Over 5.00 to 10.00, incl	0.15
	Over 10.00 to 20.00, incl	0.20
	Over 20.00 to 30.00, incl	0.25
	Over 30.00 to 40.00, incl	0.30
	Over 40.00 to 60.00, incl	0.35
	Over 60.00 to 80.00, incl	0.45
	Over 80.00 to 99.00, incl	0.60
Cobalt	Up to 0.10, incl	0.01
	Over 0.10 to 0.20, incl	0.02
	Over 0.20 to 1.00, incl	0.03
	Over 1.00 to 5.00, incl	0.05
	Over 5.00 to 10.00, incl	0.10
	Over 10.00 to 15.00, incl	0.15
	Over 15.00 to 20.00, incl	0.20
	Over 20.00 to 25.00, incl	0.25
	Over 25.00 to 30.00, incl	0.30
	Over 30.00 to 35.00, incl	0.35
	Over 35.00 to 50.00, incl	0.50
Molybdenum	Up to 1.00, incl	0.03
	Over 1.00 to 3.00, incl	0.05
	Over 3.00 to 5.00, incl	0.10
	Over 5.00 to 20.00, incl	0.15

TABLE 1 *Continued*

Element	Limit or Maximum of Specified Element, %	Variation Under min or Over max
	Over 20.00 to 30.00, incl	0.25
	Over 30.00 to 40.00, incl	0.35
Tungsten	Up to 1.00, incl	0.04
	Over 1.00 to 3.00, incl	0.10
	Over 3.00 to 5.00, incl	0.15
	Over 5.00 to 10.00, incl	0.20
	Over 10.00 to 20.00, incl	0.25
Columbium (Nb) and/or Tantalum	Up to 1.50, incl	0.05
	Over 1.50 to 3.00, incl	0.10
	Over 3.00 to 5.00, incl	0.15
	Over 5.00 to 7.00, incl	0.20
	Over 7.00 to 10.00, incl	0.25
	Over 10.00 to 13.00, incl	0.30
Titanium	Up to 0.10, incl	0.02
	Over 0.10 to 0.50, incl	0.03
	Over 0.50 to 1.00, incl	0.04
	Over 1.00 to 2.00, incl	0.05
	Over 2.00 to 3.50, incl	0.07
	Over 3.50 to 5.00, incl	0.10
	Over 5.00 to 10.00, incl	0.20
Aluminum	Up to 0.10, incl	0.02
	Over 0.10 to 0.50, incl	0.05
	Over 0.50 to 2.00, incl	0.10
	Over 2.00 to 5.00, incl	0.20
	Over 5.00 to 10.00, incl	0.25
	Over 10.00 to 15.00, incl	0.30
Boron	Up to 0.01, incl	0.002
	Over 0.01 to 0.05, incl	0.005
	Over 0.05 to 0.15, incl	0.010
Iron	Up to 0.20, incl	0.02
	Over 0.20 to 0.75, incl	0.03
	Over 0.75 to 2.50, incl	0.05
	Over 2.50 to 5.00, incl	0.07
	Over 5.00 to 10.00, incl	0.10
	Over 10.00 to 15.00, incl	0.15
	Over 15.00 to 30.00, incl	0.30
	Over 30.00 to 50.00, incl	0.45
Copper	Up to 0.20, incl	0.02
	Over 0.20 to 0.50, incl	0.03
	Over 0.50 to 5.00, incl	0.04
	Over 5.00 to 10.00, incl	0.05
	Over 10.00 to 20.00, incl	0.10
	Over 20.00 to 30.00, incl	0.15
	Over 30.00 to 40.00, incl	0.20
	Over 40.00 to 50.00, incl	0.25
Vanadium	Up to 0.50, incl	0.04
	Over 0.50 to 1.50, incl	0.05
Yttrium	Up to 0.050, incl	0.005
	Over 0.050 to 0.10, incl	0.010
	Over 0.10 to 0.20, incl	0.015
Zirconium	Up to 0.10, incl	0.01
	Over 0.10 to 0.20, incl	0.02
Lanthanum	Up to 0.20, incl	0.01
Cerium	Up to 0.050, incl	0.005
	Over 0.050 to 0.10, incl	0.010
	Over 0.10 to 0.20, incl	0.015
Hafnium	Up to 1.50, incl	0.05
	Over 1.50 to 3.00, incl	0.10
Rhenium	Up to 1.50, incl	0.05
	Over 1.50 to 3.00, incl	0.10

TABLE 1 *Continued*

Element	Limit or Maximum of Specified Element, %	Variation Under min or Over max
	Over 3.00 to 5.00, incl	0.15
	Over 5.00 to 7.00, incl	0.20
Platinum	Up to 0.50, incl	0.03
Oxygen	Up to 0.010, incl	0.005
Nitrogen	Up to 0.02, incl	0.005
	Over 0.02 to 0.19, incl	0.01
	Over 0.19 to 0.25, incl	0.02
	Over 0.25 to 0.35, incl	0.03
	Over 0.35 to 0.45, incl	0.04
	Over 0.45 to 0.60, incl	0.05
Magnesium	Up to 0.10, incl	0.01
Lead	Up to 0.01, incl	0.002
Tin	Up to 0.01, incl	0.002
	Over 0.01 to 0.05, incl	0.005
Zinc	Up to 0.01, incl	0.002
	Over 0.01 to 0.05, incl	0.005

5. Quality Assurance Provisions

5.1 *Sampling*—For the purpose of determining conformance to the chemical composition requirement, each heat or lot in a shipment shall be considered separately. All samples shall be taken from finished part or material in the condition in which it is received, except that all protective surface treatments shall be removed before sampling. Sample material shall be free from scale, grease, dirt, and other foreign materials and shall be

taken in such a manner as to prevent alteration of the chemical composition of the sample. Sampling shall be in accordance with Practice **E55** for wrought material or Practice **E88** for cast material, as applicable, insofar as practicable.

6. Keywords

6.1 cobalt alloys; nickel alloys; product check analysis

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/

TABLE 1 *Continued*

Element	Limit or Maximum of Specified Element, %	Variation Under min or Over max
	Over 3.00 to 5.00, incl	0.15
	Over 5.00 to 7.00, incl	0.20
Platinum	Up to 0.50, incl	0.03
Oxygen	Up to 0.010, incl	0.005
Nitrogen	Up to 0.02, incl	0.005
	Over 0.02 to 0.19, incl	0.01
	Over 0.19 to 0.25, incl	0.02
	Over 0.25 to 0.35, incl	0.03
	Over 0.35 to 0.45, incl	0.04
	Over 0.45 to 0.60, incl	0.05
Magnesium	Up to 0.10, incl	0.01
Lead	Up to 0.01, incl	0.002
Tin	Up to 0.01, incl	0.002
	Over 0.01 to 0.05, incl	0.005
Zinc	Up to 0.01, incl	0.002
	Over 0.01 to 0.05, incl	0.005

5. Quality Assurance Provisions

5.1 *Sampling*—For the purpose of determining conformance to the chemical composition requirement, each heat or lot in a shipment shall be considered separately. All samples shall be taken from finished part or material in the condition in which it is received, except that all protective surface treatments shall be removed before sampling. Sample material shall be free from scale, grease, dirt, and other foreign materials and shall be

taken in such a manner as to prevent alteration of the chemical composition of the sample. Sampling shall be in accordance with Practice **E55** for wrought material or Practice **E88** for cast material, as applicable, insofar as practicable.

6. Keywords

6.1 cobalt alloys; nickel alloys; product check analysis

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/



Contact ASTM

Call Us

Monday through Friday 8:30am-6:00pm Eastern
US Standard Time

Sales & Support

1-877-909-2786 (USA & Canada)

International

001-610-832-9585 (Customer Service)

001-610-832-9578 (Technical Support)

Canada Office

171 Nepean Street, Suite 400
Ottawa, ON K2P 0B4

[Diane Thompson](#)

Tel: +1.613.751.3409

Brussels Office

Rue de la Loi 67
B-1040 Brussels,
Belgium

[Sara Gobbi](#)

Tel +32.(0)2.8405127

China Office

Suite EF-09, Twin Towers East,
B-12 Jianguomenwai Ave.
Chaoyang District, Beijing, P.R. China
100022

[Liu Fei](#)

Tel: +86.10.5109.6033

Fax: +86.10.5109.6039



Contact ASTM

Call Us

Monday through Friday 8:30am-6:00pm Eastern
US Standard Time

Sales & Support

1-877-909-2786 (USA & Canada)

International

001-610-832-9585 (Customer Service)

001-610-832-9578 (Technical Support)

Media Contact

[Nathan Osburn](#), Director,
Corporate Communications
Tel: +610.832.9603