



Designation: C78/C78M – 18

Standard Test Method for Flexural Strength of Concrete (Using Simple Beam with Third-Point Loading)¹

This standard is issued under the fixed designation C78/C78M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This test method covers the determination of the flexural strength of concrete by the use of a simple beam with third-point loading.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C31/C31M Practice for Making and Curing Concrete Test Specimens in the Field

C42/C42M Test Method for Obtaining and Testing Drilled Cores and Sawed Beams of Concrete

C125 Terminology Relating to Concrete and Concrete Aggregates

C192/C192M Practice for Making and Curing Concrete Test Specimens in the Laboratory

C293/C293M Test Method for Flexural Strength of Concrete (Using Simple Beam With Center-Point Loading)

C617/C617M Practice for Capping Cylindrical Concrete Specimens

C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials

C1077 Practice for Agencies Testing Concrete and Concrete Aggregates for Use in Construction and Criteria for Testing Agency Evaluation

E4 Practices for Force Verification of Testing Machines

E6 Terminology Relating to Methods of Mechanical Testing

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this test method, refer to Terminology C125 and Terminology E6.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *flexural strength*—maximum resistance of a specimen subjected to bending.

3.2.1.1 *Discussion*—In this test method, *flexural strength* is reported as the *modulus of rupture*.

3.2.2 *flexural testing apparatus*—fixture used to apply force to the beam specimen and consists of loading and support blocks.

3.2.3 *loading block*—component of the testing apparatus in the shape of a portion of a cylinder that is used to apply a force to the beam specimen.

3.2.4 *modulus of rupture*—calculated stress, assuming linear-elastic behavior, in the tensile face of a beam specimen at the maximum bending moment during a standard test method.

3.2.5 *span length*—distance between lines of support, or reaction, for the beam specimen, and it is equal to three times the nominal depth of the beam.

3.2.5.1 *Discussion*—For example, for a 100 mm [4 in.] nominal depth beam, the span length is 300 mm [12 in.] and for a 150 mm [6 in.] nominal depth beam, the span length is 450 mm [18 in.]. See 3.2.6.1, for discussion of *reaction block*.

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.61 on Testing for Strength.

Current edition approved Jan. 1, 2018. Published February 2018. Originally approved in 1930. Last previous edition approved in 2016 as C78/C78M – 16. DOI: 10.1520/C0078_C0078M-18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2.6 *support block*—component of the testing apparatus in the shape of a portion of a cylinder that is used to provide a reaction to the force applied to the beam specimen.

3.2.6.1 *Discussion*—If the testing apparatus applies force to the top of the beam, this block supports the beam. If the testing apparatus applies force to the bottom of the beam, the support block may be considered a reaction block because it provides a line of reaction at the top of the beam and does not support the beam.

3.2.7 *testing machine*—mechanical device for applying force to a specimen.

4. Significance and Use

4.1 This test method is used to determine the flexural strength of specimens prepared and cured in accordance with Test Methods C42/C42M or Practices C31/C31M or C192/C192M. Results are calculated and reported as the modulus of rupture. For the same specimen size, the strength determined will vary if there are differences in specimen preparation, curing procedure, moisture condition at time of testing, and whether the beam was molded or sawed to size.

4.2 The measured modulus of rupture generally increases as the specimen size decreases.^{3,4,5}

4.3 The results of this test method may be used to determine compliance with specifications or as a basis for mixture proportioning, evaluating uniformity of mixing, and checking placement operations by using sawed beams. It is used primarily in testing concrete for the construction of slabs and pavements.

4.4 For identical test specimens, the modulus of rupture obtained by this test method will, on average, be lower than that obtained by Test Method C293/C293M.

5. Apparatus

5.1 *Testing Machine*—Hand operated testing machines having pumps that do not provide a continuous loading in one stroke are not permitted. Motorized pumps or hand operated positive displacement pumps having sufficient volume in one continuous stroke to complete a test without requiring replenishment are permitted and shall be capable of applying loads at a uniform rate without shock or interruption. The testing machine shall be equipped with a means of recording or holding the peak value that will indicate the maximum load, to within 1 % accuracy, applied to the specimen during a test.

5.1.1 Verification:

5.1.1.1 The testing machine shall conform to the requirements of the sections on Basis of Verification, Corrections, and Time Interval Between Verifications of Practice E4.

5.1.1.2 Verify the accuracy of the testing machine in accordance with Practice E4, except that the verified loading range shall be as required for flexural testing. Verification is required:

- (1) Within 13 months of the last verification,
- (2) On original installation,
- (3) After relocation,

(4) After making repairs or adjustments that affect the operation of the force applying system or the values displayed on the load indicator, except for zero adjustments that compensate for the weight of loading or support blocks or specimen, or both, or

(5) Whenever there is reason to suspect the accuracy of the indicated forces.

5.2 *Flexural Testing Apparatus*—The third point loading method shall be used to determine the flexural strength of concrete. The loading blocks and support blocks shall be designed so that forces applied to the beam will be along lines perpendicular to the side faces of the beam and applied without eccentricity. A diagram of the flexural testing apparatus is shown in Fig. 1.

NOTE 1—The flexural testing apparatus shown in Fig. 1 may be used inverted. In this case, the loading blocks will be at the bottom of the beam, while the reaction blocks will be at the top of the beam.

5.2.1 The flexural testing apparatus shall be capable of maintaining the span length and distance between the lines of loading within ± 1.0 mm [± 0.05 in.] of the specified values.

5.2.2 The ratio of the horizontal distance between the line of application of the force and the line of the nearest reaction to the depth of the beam shall be 1.0 ± 0.03 .

5.2.3 The loading blocks and support blocks shall not be more than 65 mm [2.50 in.] high, measured from the center or the axis of the ball or the axis of the rod and shall extend entirely across or beyond the full width of the specimen. Each case, the block surface in contact with the specimen shall not depart from a plane by more than 0.05 mm [0.002 in.] and shall be a portion of a cylinder, the axis of which is coincidental with either the axis of the rod or center of the ball, whichever the block is pivoted upon. The angle subtended by the curved surface of each block shall be at least 0.80 rad [45°].

5.2.4 At least every six months or as specified by the manufacturer of the flexural testing apparatus, clean and lubricate metal-to-metal contact surfaces, such as internal concave surfaces and steel balls and rods of the loading blocks and support blocks (Fig. 1). The lubricant shall be a petroleum-type oil, such as conventional motor oil, or as specified by the manufacturer of the apparatus.

5.2.5 The support blocks shall be free to rotate.

5.2.6 The loading blocks and support blocks shall be maintained in a vertical position and in contact with the rod or ball by means of spring-loaded screws that hold them in contact with the rod or ball. The uppermost bearing plate and center point ball in Fig. 1 may be omitted if the testing machine has a spherically seated bearing block, provided one rod and one ball are used as pivots for the upper loading blocks.

³ Tanesi, J; Ardani, A. Leavitt, J. "Reducing the Specimen Size of Concrete Flexural Strength Test (AASHTO T97) for Safety and Ease of Handling," *Transportation Research Record: Journal of the Transportation Research Board*, No. 2342, Transportation Research Board of National Academies, Washington, D.C., 2013.

⁴ Carrasquillo, P.M. and Carrasquillo, R. L. "Improved Concrete Quality Control Procedures Using Third Point Loading", *Research Report 119-1F*, Project 3-9-87-1119, Center For Transportation Research, The University of Texas at Austin, November 1987.

⁵ Bazant, Z. and Novak, D. "Proposal for Standard Test of Modulus of Rupture of Concrete with its Size Dependence," *ACI Materials Journal*, January-February 2001.




FIG. 1 Schematic of Flexural Testing Apparatus for Third-Point Loading Method

6. Test Specimens

6.1 The test specimen shall conform to all requirements of Test Method C42/C42M or Practices C31/C31M or C192/C192M applicable to beam specimens and shall have a test span within 2 % of being three times its depth as tested. The sides of the specimen shall be at right angles with the top and bottom. All surfaces shall be smooth and free of scars, indentations, holes, or inscribed identification marks.

6.2 Provided the smaller cross-sectional dimension of the beam is at least three times the nominal maximum size of the coarse aggregate, the modulus of rupture can be determined using different specimen sizes. However, measured modulus of rupture generally increases as specimen size decreases.^{3,4} (Note 2).

NOTE 2—The strength ratio for beams of different sizes depends primarily on the maximum size of aggregate.⁵ Experimental data obtained in two different studies have shown that for maximum aggregate size between 19.0 and 25.0 mm [$\frac{3}{4}$ and 1 in.], the ratio between the modulus of rupture determined with a 150 by 150 mm [6 by 6 in.] and a 100 by 100 mm [4 by 4 in.] may vary from 0.90 to 1.07³ and for maximum aggregate size between 9.5 and 37.5 mm [$\frac{3}{8}$ and 1½ in.], the ratio between the modulus of rupture determined with a 150 by 150 mm [6 by 6 in.] and a 115 by 115 mm [4.5 by 4.5 in.] may vary from 0.86 to 1.00.⁴

6.3 The specifier of tests shall specify the specimen size and number of specimens to be tested to obtain an average test result. The same specimen size shall be used for qualification and acceptance testing.

7. Procedure

7.1 Moist-cured specimens shall be kept moist during the period between removal from moist storage and testing.

NOTE 3—Surface drying of the specimen results in a reduction in the measured flexural strength.

NOTE 4—Methods for keeping the specimen moist include wrapping in moist fabric or matting and keeping specimens under lime water in containers near the flexural testing machine until time of testing.

7.2 For molded specimens, turn the test specimen on its side with respect to its position as molded and center it on the

support blocks. When using sawed specimens, position the specimen so that the tension face corresponds to the top or bottom of the specimen as cut from the parent material. Center the loading blocks in relation to the applied force. Bring the loading blocks in contact with the surface of the specimen at the third points and apply a force of between 3 and 6 % of the estimated ultimate force. Using 0.10 mm [0.004 in.] and 0.40 mm [0.015 in.] leaf-type feeler gages, determine whether any gap between the specimen and the loading or support blocks is greater or less than each of the gages over a length of 25 mm [1 in.] or more. Grind, cap, or use leather shims on the specimen contact surface to eliminate any gap in excess of 0.10 mm [0.004 in.] in width. Leather shims shall be of uniform 6 mm [0.25 in.] thickness, 25 to 50 mm [1.0 to 2.0 in.] width, and shall extend across the full width of the specimen. Gaps in excess of 0.40 mm [0.015 in.] shall be eliminated only by capping or grinding. Grinding of lateral surfaces shall be minimized because grinding may change the physical characteristics of the specimens. Capping shall be in accordance with the applicable sections of Practice C617/C617M.

7.3 Load the specimen continuously and without shock. The load shall be applied at a constant rate to the breaking point. Apply the load at a rate that constantly increases the maximum stress on the tension face between 0.9 and 1.2 MPa/min [125 and 175 psi/min] until rupture occurs. The loading rate is calculated using the following equation:

$$r = \frac{Sbd^2}{L} \quad (1)$$

where:

- r = loading rate, N/min [lb/min],
- S = rate of increase in maximum stress on the tension face, MPa/min [psi/min],
- b = average width of the specimen as oriented for testing, mm [in.],
- d = average depth of the specimen as oriented for testing, mm [in.], and

L = span length, mm [in.].

8. Measurement of Specimens After Test

8.1 To determine the dimensions of the specimen cross section for use in calculating modulus of rupture, take measurements across one of the fractured faces after testing. The width and depth are measured with the specimen as oriented for testing. For each dimension, take one measurement at each edge and one at the center of the cross section. Use the three measurements for each direction to determine the average width and the average depth. Take all measurements to the nearest 1 mm [0.05 in.]. If the fracture occurs at a capped section, include the cap thickness in the measurement.

9. Calculation

9.1 If the fracture initiates in the tension surface within the middle third of the span length, calculate the modulus of rupture as follows:

$$R = \frac{PL}{bd^2} \quad (2)$$

where:

R = modulus of rupture, MPa [psi],
 P = maximum applied load indicated by the testing machine, N [lbf],
 L = span length, mm [in.],
 b = average width of specimen, mm [in.], at the fracture, and

d = average depth of specimen, mm [in.], at the fracture.

NOTE 5—The weight of the beam is not included in the above calculation.

9.2 If the fracture occurs in the tension surface outside of the middle third of the span length by not more than 5 % of the span length, calculate the modulus of rupture as follows:

$$R = \frac{3Pa}{bd^2} \quad (3)$$

where:

a = average distance between line of fracture and the nearest support measured on the tension surface of the beam, mm [in.].

NOTE 6—The weight of the beam is not included in the above calculation.

9.3 If the fracture occurs in the tension surface outside of the middle third of the span length by more than 5 % of the span length, discard the results of the test.

10. Report

10.1 Report the following information:

- 10.1.1 Identification number,
- 10.1.2 Average width to the nearest 1 mm [0.05 in.],
- 10.1.3 Average depth to the nearest 1 mm [0.05 in.],
- 10.1.4 Span length in mm [in.],
- 10.1.5 Maximum applied load in N [lbf],
- 10.1.6 Modulus of rupture calculated to the nearest 0.05 MPa [5 psi],
- 10.1.7 Curing history and apparent moisture condition of the specimens at the time of test,

10.1.8 If specimens were capped, ground, or if leather shims were used,

10.1.9 Whether sawed or molded and defects in specimens, and

10.1.10 Age of specimens.

11. Precision and Bias

11.1 Precision:

11.1.1 *Single-Operator Precision*—The single operator standard deviation for test determinations has been found to be 0.25 MPa [37 psi] and to be independent of the beam sizes used in the interlaboratory study (ILS) (Note 7). Therefore, the modulus of rupture from two properly conducted tests by the same operator on specimens of the same material (same batch of concrete), using the same size specimen (100-mm [4-in.] or 150-mm [6-in.] deep beams), is not expected to differ by more than 0.72 MPa [104 psi].⁶

11.1.2 *Multi-Laboratory Precision*—The multilaboratory coefficient of variation for test determinations has been found to be as shown in the third column of Table 1. The coefficient of variation was found to be similar for both specimen sizes used in the ILS for modulus of rupture between 4.2 and 5.5 MPa [600 and 800 psi]. A higher multilaboratory coefficient of variation was observed for 100-mm [4-in.] deep beams for modulus of rupture near 6.9 MPa [1000 psi]. Therefore, the modulus of rupture from two properly conducted tests by two different laboratories on specimens of the same material (same batch of concrete) and beam size are not expected to differ from each other by more than the value in the fourth column of Table 1. The acceptable difference between two test determinations is expressed as a percentage of their average.

NOTE 7—The precision of this test method was determined from an interlaboratory study conducted in 2016. The study involved three concrete mixtures with modulus of rupture values of approximately 4.1 MPa [600 psi], 5.5 MPa [800 psi] and 6.9 MPa [1000 psi]. Two beam sizes were used: 100 by 100 by 355 mm [4 by 4 by 14 in.] and 150 by 150 by 533 mm [6 by 6 by 21 in.]. Three test determinations were conducted for each combination of specimen size and concrete mixture. The number of laboratories used for determining the precision varied from 10 to 17 depending on the concrete mixture and beam size. The data used to develop the precision statement were obtained using the inch-pound

⁶ This number represents the difference limit (d2s) as described in Practice C670.

TABLE 1 Multilaboratory Precision

Beam Depth, in. [mm]	Modulus of Rupture, psi [MPa]	Coefficient of Variation	Acceptable Difference Between Two Test Determinations (percentage of their average) ⁴
100 mm [4 in.]	4.1 to 5.5 MPa [600 to 800 psi]	6.1 %	17.1 %
100 mm [4 in.]	6.9 MPa [1000 psi]	11.4 %	31.8 %
150 mm [6 in.]	4.1 to 6.9 MPa [600 to 1000 psi]	6.9 %	19.3 %

⁴These numbers represent the difference limit (d2s%) as described in Practice C670.

version of this test method. The precision indexes shown in SI units are exact conversions of the values in inch-pound units. Supporting data have been filed at ASTM Headquarters and may be obtained by requesting Research Report RR:C09-1050.⁷

NOTE 8—The results for each test condition (specimen size and concrete strength) include data from 3 to 5 laboratories that used hand operated testing machines with paper charts for reading the ultimate force. For the 100-mm [4-in.] deep beams, these machines resulted in higher single-operator variability in mixtures with strengths between 4.1 to 5.5

MPa [600 and 800 psi], as well as higher multilaboratory variability in all mixtures. For the 150-mm [6-in.] deep beams, these machines resulted in higher variability only for the mixture with flexural strength of approximately 6.9 MPa [1000 psi]. Refer to Research Report RR:C09-1050 (Appendix J) for a discussion of possible reasons why these machines may have resulted in higher variability.

11.2 *Bias*—Because there is no accepted standard for determining bias in this test method, no statement on bias is made.

12. Keywords

12.1 beams; concrete; flexural strength testing; modulus of rupture

⁷ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:C09-1050. Contact ASTM Customer Service at service@astm.org.

SUMMARY OF CHANGES

Committee C09 has identified the location of selected changes to this test method since the last issue, C78/C78M – 16, that may impact the use of this test method. (Approved Jan. 1, 2018.)

- | | |
|---|---|
| <ul style="list-style-type: none"> (1) Revised Sections 2 and 7.2. (2) Added Sections 3 and 4.4. (3) Revised 5.1. (4) Added 5.1.1. (5) Revised 5.2 and its subsections. (6) Revised Fig. 1. | <ul style="list-style-type: none"> (7) Added Note 1. (8) Deleted existing Notes 2, 7, and 8. (9) Revised 4.2, 6.3, and 11.1. (10) Added Table 1 and Notes 7 and 8. (11) Added 5.2.4. |
|---|---|

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>